

PRODUCT DATA SHEET

SikaCeram®-125 Easy Fix IN

High polymer based cementitious tile adhesive with special bonding additives for vitrified and ceramic tiles with no vertical slip (Type-2 'T', C1TE Adhesive)

DESCRIPTION

SikaCeram®-125 Easy Fix IN is a high polymer modified, cementitious, normal setting, self curing, easy fixing floor and wall tile adhesive. For small, medium sized ceramic and vitrified tiles in residential environments. Suitable for bonding absorbent and partly absorbent ceramic tiles to absorbent construction material substrates. For Indoor use.

USES

Bonding the following types of tiles:

- Vitrified
- Ceramic

Bonding tiles for the following applications:

- Balconies
- Bathrooms
- Kitchens
- Residential environments
- Terraces
- Wet areas
- Tile on tile in any of above areas

CHARACTERISTICS / ADVANTAGES

Layer thickness 3mm (Minimum)

- Reduced vertical slip
 - Smooth application
 - Easy to use, only water to be added
 - Better bond than conventional cement based mortar
 - Self curing
 - Bonding floor and wall tiles
 - Suitable for absorbent ceramic tiles and vitrified tiles
- Typical bonding substrates: Cementitious screed, concrete, plaster, ceramic tiles

APPROVALS / STANDARDS

Conforms to IS 15477-2019 , Type-2 'T' Adhesive

Conforms to EN12004-1 :2017, C1TE Class Adhesive

PRODUCT INFORMATION

Chemical base	Portland cement, selected aggregates, water retention additives, re-dispersible polymer
Packaging	20 kg bag and 40 kg bag
Appearance / Colour	Grey powder
Shelf life	12 months from date of production
Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +35 °C.

TECHNICAL INFORMATION

Tensile adhesion strength	Test Condition	Requirement as per Standard	Values Observed (EN 12004-2: 2017)
	Initial / dry condition	$\geq 0.5 \text{ N/mm}^2$	$\geq 1.0 \text{ N/mm}^2$
	After water immersion/ wet condition	$\geq 0.5 \text{ N/mm}^2$	$\geq 0.8 \text{ N/mm}^2$
	After heat ageing	$\geq 0.5 \text{ N/mm}^2$	$\geq 0.7 \text{ N/mm}^2$
	After > 30 minutes, open time	$\geq 0.5 \text{ N/mm}^2$	$\geq 0.5 \text{ N/mm}^2$
	Test Condition	Requirement as per Standard	Values Observed (IS 15477-2019)
	Dry condition	$\geq 1.0 \text{ N/mm}^2$	$\geq 1.2 \text{ N/mm}^2$
	Wet condition	$\geq 1.0 \text{ N/mm}^2$	$\geq 1.0 \text{ N/mm}^2$
Slip resistance	Requirement as per Standard	Value Observed	(EN12004-2 :2017)
	$\leq 0.5 \text{ mm}$	$\leq 0.25 \text{ mm}$	

APPLICATION INFORMATION

Mixing ratio	Packing	Water to powder ratio by weight	Quantity of water per bag
	20 kg, Grey	0.20–0.25	4.0–5.0 Lt
	40 kg, Grey	0.20–0.25	8.0–10.0 Lt

Consumption	Consumption is dependent on the substrate, surface profile, roughness, size of the tiles, the joints between them and application technique (i.e. single spreading / floating method or double spreading / buttering method). Apply product to a test area to calculate the exact consumption for the specific substrate conditions and proposed application. As a guide for a single adhesive layer:		
	Size of tiles	Bed thickness	Consumption (Grey) dry powder
	Small	3 mm	3.00–3.50 kg/m ²
	Medium	4 mm	4.25–4.75 kg/m ²
	Large	5 mm	5.00–5.50 kg/m ²

Ambient air temperature	+5 °C min. / +45 °C max.	
Substrate temperature	+5 °C min. / +45 °C max.	
Pot life	≥ 180 minutes (100 g mass, +27 °C)	
Open time	> 30 min (EN 12004-2 / ISO 13007-2)	
Applied product ready for use	Use	Waiting time
	Grouting floors / walkability	≈ 24 hours @ 30°C

Adjustability time	~ 25 min (+27 °C)		
Fresh mortar density	Grey	1.7 ± 0.2 kg/L (+27 °C)	(EN ISO 2811-1)

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

Important: Do not apply on metal surfaces, wood and old ceramic tiles outdoor.

Important: Gypsum plaster and anhydrite screed substrates must have a maximum moisture content of 0.5%.

Important: Cementitious substrates must be cured and dried for minimum 28 days

The substrate can be one of the following materials: Cementitious screed, concrete, plaster, ceramic tiles, cement lime mortars, calcium sulphate screed, gypsum fibre boards.

- All substrates must be structurally sound, able to support the weight of the new tiling and provide a firm and securely fixed background.
- Substrates must be clean, dry, free of any loose or friable particles, contaminants such as dust, dirt, oil, wax polish, grease, cement laitance or efflorescence.
- Use adequate mechanical preparation techniques to remove from the substrate, all traces of any materials that could reduce the product's adhesion to the substrate.
- Smooth surfaces must be roughened lightly to improve adhesion.
- To confirm adequate surface preparation and adhesion, carry out a small trial before full application.
- Any small surface defects and variations in level, profile, or around exposed aggregates, prefill and level with an additional layer of SikaCeram®-125 Easy Fix IN to a maximum thickness of 5 mm, applied at least 24 hours before full adhesive application.
- For larger and thicker areas of substrate re-profiling and making good, use suitable mortars from the Sika MonoTop® or SikaCeram® Floor Leveler range.
- Identify cracks in the substrate and seal appropriately with Sikadur® epoxy resins.
- When laying tiles on non-absorbent or substrates with limited absorbency, such as existing ceramic

tiles, painted surfaces etc., check these surfaces are all sound, firm and securely bonded. Use suitable degreasing / descaling products to thoroughly and completely clean the substrate.

- For applications in hot climates / environments, or on absorbent substrates, thoroughly pre-dampen the substrate immediately before product application.
- Avoid any ponding / standing water on the substrate.
- If a waterproofing layer is required under the tiles, cement-based and acrylic-based Sika® waterproofing product / systems must be applied to the substrate before tiling.

MIXING

Important: Avoid over-mixing to minimise air entrainment.

Requirement: Use a low speed electric single paddle mixer (< 500 rpm) with spiral paddle for mixing.

- Pour the minimum recommended quantity of clean cold water into a clean mixing container.
- Gradually add SikaCeram®-125 Easy Fix IN powder to the water while mixing.
- Mix thoroughly for ~5 minutes until a uniformly coloured, smooth mix is achieved. Add additional water, if necessary, to the maximum specified amount.
- Do not mix for ~5 minutes to allow mixed product to 'mature'.
- Remix for ~15 seconds.

APPLICATION

Important: Apply sufficient adhesive to ensure adequate 'wetting' of the backs of the tiles.

Important: Coverage on the back of the tiles must be 100 %.

Important: Tiling must be carried out on freshly applied adhesive. Exert adequate pressure to ensure 100% complete and uniform contact with the adhesive to achieve optimum adhesion.

Important: If a skin forms on the surface of the adhesive, immediately remove the adhesive layer with a trowel, discard material and apply a fresh layer of SikaCeram®-125 Easy Fix IN adhesive.

Important: Protect freshly applied material from freezing conditions and rain, etc.

Important: For natural stone tiles, always carry out a preliminary test application first.

Note: For tiles > 900 cm² (e.g. 30 × 30 cm), the double spreading (buttering) technique is always recommended.

Apply sufficient adhesive to the prepared fixing surfaces with the flat side of trowel.

- Comb additional adhesive with appropriate square

- notched trowel to the required bed thickness.
- Wherever needed (for large tiles), back butter the tiles for full bedding.
- Place tiles into wet, sticky adhesive and use rubber mallet to fully embed the tiles.
- Adjust tiles if required. Provide support wherever needed.
- Clean off surplus adhesive from tile face and between tile joints before the adhesive has dried.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.

620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
West Bengal, India

Contact:

Phone: +91 33 2447 2448
Fax: +91 33 2397 8688
info.india@in.sika.com
www.sika.in



Product Data Sheet

SikaCeram®-125 Easy Fix IN
June 2026, Version 02.01
021710102000246018

SikaCeram-125EasyFixIN-en-IN-(06-2026)-2-1.pdf