

PRODUCT DATA SHEET

SikaCeram[®]-255

HIGH PERFORMANCE CEMENT BASE ADHESIVE WITH NO VERTICAL SLIP AND EXTENDED OPEN TIME. C2TE CLASSIFIED ACCORDING TO EN 12004

DESCRIPTION

High performance cement base adhesive with no vertical slip and extended open time for fixing Vitrified Tiles, Glass Mosaic and Natural Stone. C2TE classified according to EN 12004

USES

- Laying all kind of vitrified tiles, glass mosaic and natural stone.
- Laying marble and natural stone, provided not sensitive to water
- Indoor and outdoor, on walls and floors
- Indoor over-tiling applications on old tiles, without primer
- Suitable for applications where high performance is demanded, such as swimming pools, industrial and heavy trafficked floors

CHARACTERISTICS / ADVANTAGES

- No vertical slipping
- Extended open time
- Application upto 10 mm thick

APPROVALS / STANDARDS

One-pack improved cement base adhesive. Particularly suitable for Vitrified and natural stones. Use on heating floor surfaces, industrial floors and swimming pools. EN12004 class C2TE.

PRODUCT INFORMATION

Packaging	25 kg bag
Appearance / Colour	Grey and White powder
Shelf Life	12 months from date of production.
Storage Conditions	12 months from date of production if stored properly in undamaged original sealed packaging, in dry cooled conditions.
Density	Grey : 1.32 kg/l (Bulk Density) White : 1.18 kg/l (Bulk Density)

Tensile Adhesion Strength	Value Grey	Value White	Requirement EN 12004	Test Method
Initial Tensile Bond	1.9 N/mm ²	1.8 N/mm ²	≥ 1.0 N/mm ²	EN 1348
Tensile Bond after heat ageing	1.2 N/mm ²	1.2 N/mm ²	≥ 1.0 N/mm ²	EN 1348
Tensile Bond after water immersion	1.4 N/mm ²	1.5 N/mm ²	≥ 1.0 N/mm ²	EN 1348
Slip Resistance	Value Grey	Value White	EN 12004	Test Method
Slip Resistance	≤ 0.5 mm	≤ 0.5 mm	≤ 0.5 mm	EN 1308
Mixing Ratio	~6.5-7 ltrs of water (26%-28%) for 25kg of SikaCeram-255 Grey ~6.75-7.25 ltrs of water (27%-29%) for 25kg of SikaCeram-255 White			
Consumption	The consumption is dependent on the surface profile and roughness of the substrate as well as on the size of the tiles and the application technique (double-spreading, in thin-bed consistency, or single-spreading, in flow-bed consistency). As a guide, in kilograms of powder per m ² : 1.2 kg / m ² / mm of thickness			
Layer Thickness	10 mm max			
Ambient Air Temperature	±5°C min; ±35°C max			
Substrate Temperature	±5°C min; ±35°C max			
Pot Life	~3-4 hours at 23°C			
Open Time	~30 minutes at 23°C (EN 1346)			
Adjustability Time	~40 minutes at 23°C			

SUBSTRATE QUALITY / PRE-TREATMENT

The substrate must be cement laitance free, clean and free from dirt, oil, grease or other contaminants and loose or friable particles. The substrate must be perfectly flat, sound and free from parts easily removed, non-deformable and correctly aged. Any small gradients or bumps can be levelled/filled with a layer of SikaCeram-255 in a maximum thickness of 5 mm, applied at least 24 hours before laying the ceramic coating. For builds greater than 10mm thick, use the appropriate Sika MonoTop® or Sika® Level product(s).

SikaCeram-255 is applied directly on plasters and cementitious substrates, cement-lime mortars, concrete, plasterboard, floater finished concrete and old ceramic floors.

MIXING

Mix the contents of a 25 kg bag with the required amount of water (as specified above), using an electric mixer and a suitable mixing spiral at low speed, in a clean bucket. Do not exceed a mixing speed of 500 rpm as doing so may reduce the final strength of the cured product. Mix to obtain a smooth paste free of lumps. After mixing, leave the product for 5 minutes, and then briefly stir the mixture prior to application. This should result in a very creamy, easily spreadable, and highly thixotropic adhesive.

APPLICATION

SikaCeram-255 is applied using a notched trowel. The amount of product should be enough to ensure complete wetting of the tile. Tiling has to be carried out on fresh adhesive, exerting an adequate pressure to ensure contact with the adhesive to form a full bond. If a surface film has formed on the adhesive, it is necessary to trowel over the previously applied adhesive layer. Avoid wetting the adhesive already applied with water.

To lay tiles sized 900 cm² (e.g. 30 x 30 cm) or larger, the double-spreading (Back buttering) thin-bed consistency or single-spreading flow-bed consistency techniques of adhesive application is always recommended.

If the substrate is very porous, if the temperature is high and/or the relative humidity low, it is advisable to dampen the surface. Do not leave any standing water.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened material can only be mechanically removed.

FURTHER DOCUMENTS

SikaCeram®-255 shall not be applied in the following cases:

- On metal surfaces and wood

LIMITATIONS

All technical data stated in this Product Data Sheet is based on laboratory tests. Actual measured data may vary due to circumstances beyond our control. Values achieved in laboratory conditions: 23°C ± 2°C – R.H. 50% ± 5%. Higher temperatures reduce the indicated lapse time, oppositely, lower temperatures increase them.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.

620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
Tel : +91 33 24472448
Fax : +91 33 23978688
Mail : info.india@in.sika.com



Product Data Sheet
SikaCeram®-255
August 2019, Version 01.02
020404020010000004

SikaCeram-255-en-IN-(08-2019)-1-2.pdf