

## PRODUCT DATA SHEET

# Sikalastic®-853 R AP

Hybrid polyurea hot spray applied membrane for roof waterproofing

### DESCRIPTION

Sikalastic®-853 R AP is a 2-part, hybrid polyurea, hot spray applied, crack-bridging, roof waterproofing membrane. It requires an aliphatic top coat when applied to fully exposed roofs.

### USES

Sikalastic®-853 R AP may only be used by experienced professionals.

Designed for the following waterproofing applications:

- Flat and sloping fully exposed roofs to UV, protected by an aliphatic topcoat
- New construction and refurbishment projects
- Balcony and terrace decks underneath a protective layer (i.e. ballast, paving slabs, tiles)
- Waterproofing membrane for concrete, metal, pedestrian decks, stadium seating floor application
- For exterior use only

### CHARACTERISTICS / ADVANTAGES

- Fast curing, seamless finish
- Good elasticity and elongation at break
- Fast application
- Applied by 2-component hot spray equipment
- Easily detailed around complex geometries
- Good chemical resistance
- Good adhesion to many substrates with the appropriate primers
- Thickness: ~1.5–2.0 mm

### APPROVALS / STANDARDS

- Sikalastic®-853 R AP is in conformance with JIS A 6021

### PRODUCT INFORMATION

<b>Chemical base</b>	Polyurethane/Polyurea Hybrid	
<b>Packaging</b>	Part A (Isocyanate)	200 kg drum
	Part B (Polyol mix)	175 kg drum
	Part C (Sika® Toner PU)	15 kg container
<b>Shelf life</b>	12 months from date of production	
<b>Storage conditions</b>	Product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.	
<b>Colour</b>	Part A	~Clear / brownish
	Part B	~Amber
	Part C	Grey No.12 (~RAL 7011)

Density	Part A	1.0 kg/L
	Part B	1.0 kg/L
	Part C	1.25 kg/L
	Mixed resin	1.01 kg/L

Values at +23 °C

Solid content by weight > 99 %

## TECHNICAL INFORMATION

Shore A hardness	~79 (7 days / +23 °C)	(JIS K6253)
Tensile strength	~10 N/mm <sup>2</sup> (7 days / +23 °C)	(JIS A6021)
Elongation at break	~510 % (7 days / +23 °C) Elastic properties are maintained at temperatures down to -20 °C	(JIS A6021)
Tear strength	~58 N/mm (7 days / +23 °C)	(JIS A6021)
Chemical resistance	Resistant to many chemicals. Contact Sika Technical Services for additional information.	
Artificial Ageing	Limited resistance to UV-induced degradation	

## SYSTEM INFORMATION

### System structure

### Sikalastic®-853 R AP roof waterproofing systems

Note: Sikalastic®-853 R AP can be applied in different roof system build ups for concrete, metal or asphalt substrates. Contact Sika Technical Services for additional information.

Layer	Product	Consumption
1. Primer	Depending on the substrate (Concrete, Metal, Asphalt)	Refer to individual Product Data Sheet
2. Base Coat	Sikalastic®-853 R AP (coloured)	~2.00 kg/m <sup>2</sup>
3. Top Coat	Sikalastic® ExcelTop High Reflection	~0.2 kg/m <sup>2</sup>
	Sikalastic® U-Coating (concrete substrates)	~0.2 kg/m <sup>2</sup>

These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level and wastage, etc.

### Primers

Substrate	Primer
Concrete	Sika® Concrete Primer or Sikalastic®-10 Primer EP or Sika® Primer PW-F
Metal	Sikalastic® Metal Primer or Sikalastic®-10 Primer EP or Sika® Primer PW-F
Asphalt	Sikalastic® Metal Primer or Sikalastic®-10 Primer EP or Sika® Lance-Lock Sheet

Dry film thickness ~1.5–2.0 mm depending on the system

## APPLICATION INFORMATION

Mixing ratio Part A : Part B + Part C = 1 : 1 (by volume)

**Product temperature**

**Important:** Make spray equipment fine temperature adjustments to obtain equal output pressures of the 2 parts.

Note: Higher temperatures provide lower viscosity and lower pressure.

Part A (Isocyanate) ~55 °C

Part B (Polyol mix) ~66 °C

**Ambient air temperature**

+5 °C min. / +35 °C max.

**Relative air humidity**

85 % max.

**Dew point**

Beware of condensation.

The substrate and uncured applied membrane must be at least +3 °C above dew point.

**Substrate temperature**

+5 °C min. / +35 °C max.

**Substrate moisture content**

≤ 4 % parts by weight.

The following test methods can be used: Sika®-Tramex meter, CM-measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).

**Waiting time / Overcoating**

**Important:** If the maximum waiting time is exceeded then Sika® Sokan Primer-J must be applied as a bonding bridge.

Before applying Sikalastic® U-Coating or ExcelTop High Reflection on Sikalastic®-853 R AP allow:

Substrate temperature	Minimum	Maximum*
+10 °C	~90 minutes	~3 hours
+20 °C	~60 minutes	~2 hours
+30 °C	~30 minutes	~2 hours
+45 °C	~20 minutes	~1 hours

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

**Drying time**

Cup Gel Test: Gel time (+25 °C) starts after ~20 seconds.

**Applied product ready for use**

Temperature	Rain Resistant	Foot Traffic
+10 °C	~5 minutes	~90 minutes
+20 °C	~5 minutes	~60 minutes
+30 °C	~5 minutes	~30 minutes
+45 °C	~5 minutes	~20 minutes

Foot traffic applies only for inspection or application of next layer.

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

**BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

**FURTHER DOCUMENTS**

Refer to the Sika Method Statement: Sikalastic®-853 R AP

**IMPORTANT CONSIDERATIONS**

Installation work must only be carried out by Sika® trained and approved contractors, experienced in this type of application.

Refer to the Sika Method Statement: Sikalastic®-853 R AP

**ECOLOGY, HEALTH AND SAFETY**

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

**APPLICATION INSTRUCTIONS****EQUIPMENT**

Refer to the Sika Method Statement: Sikalastic®-853 R AP

## SUBSTRATE PREPARATION

The supporting structure must be of sufficient structural strength to apply all new and existing layers of the roof build-up. Complete roof system must be designed and secured against wind uplift loadings. Refer to the Sika Method Statement: Sikalastic®-853 R AP

## MIXING

Refer to the Sika Method Statement: Sikalastic®-853 R AP

## APPLICATION

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Refer to the Sika Method Statement: Sikalastic®-853 R AP

## CLEANING OF TOOLS

Clean all tools and application equipment with Thinner C immediately after use. Hardened material can only be removed mechanically.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika India Pvt. Ltd.**  
620, Diamond Harbour Road  
Commercial Complex II  
Kolkata - 700 034  
West Bengal, India

**Contact:**  
Phone: +91 33 2447 2448  
Fax: +91 33 2397 8688  
info.india@in.sika.com  
www.sika.in



**Product Data Sheet**  
Sikalastic®-853 R AP  
May 2022, Version 02.01  
020915601000000019

Sikalastic-853RAP-en-IN-(05-2022)-2-1.pdf