

PRODUCT DATA SHEET

Sika® Stabilizer-1 HC IN

High performance compaction aid for semi-dry / no-slump concrete products

DESCRIPTION

Sika® Stabilizer-1 HC IN is a very efficient high-performance compaction aid for semi-dry/ no-slump concrete. This innovative admixture technology has been specifically developed for use in low cement content semi-dry/ no-slump mixes.

USES

Sika® Stabilizer-1 HC IN is used for producing optimised coloured and grey semi-dry/no-slump concrete with a very low moisture content. Semi-dry/no-slump concrete production is generally used in the manufacture of machine-made concrete products associated with instant de-moulding such as:

- Block Paving (grey/coloured)
- Paving flags
- Kerbstones
- Edgings and other items for garden and landscape design
- Building blocks and bricks
- Concrete pipes
- Manhole and drainage goods
- Semi-dry pressed and hollow core slabs
- Semi-dry pressed precast elements

CHARACTERISTICS / ADVANTAGES

Sika® Stabilizer-1 HC IN offers substantial benefits to the producer of semi-dry/no-slump concrete products:

- Efficient dispersion and distribution of cement, additives and pigments
- Improved movement of the concrete through the machine (faster mould filling)
- Optimised compaction with shorter pressing time and increased throughput (shorter production cycle)
- Minimized friction between the mould and the concrete (reductions in equipment wear and tear)
- Reduced adhesion/stickiness between top layer concrete and pressing head/tamper (equipment/tools)
- Increased "green" strength on immediate de-moulding (keeps the shape of freshly de-moulded semi-dry concrete products because it prevents slumping after de-moulding)
- More economic concrete mix designs
- Create superior products

Sika® Stabilizer-1 HC IN allows for the following advantages in the finished concrete products:

- Closer textured, smoother and more uniform surfaces (improved surface finish)
- Consistent product quality due to a homogenous concrete mix
- Increased density
- Less variation in densities and strengths across the area of the mould (constant spread of density & strength over the pallet)
- Minimized damage due to early handling
- Enhanced early and ultimate compressive and tensile strengths
- Increased freeze-thaw resistance
- Improved durability and life expectancy

PRODUCT INFORMATION

Chemical base	Surfactant blends
Packaging	230 kg drums

Shelf life	12 months from date of production if stored properly in undamaged unopened, original sealed packaging.
Storage conditions	Store in dry conditions at temperatures between +10°C and +40°C. Protect from direct sunlight and frost.
Appearance / Colour	Light Brown Liquid
Density	~1.06 kg/l (at 25°C)
pH-Value	≥ 6
Recommended Dosage	0.2% - 1% of cement/cementitious weight. Actual dosage to be decided on the basis of site trials with available ingredients.
Dispensing	Sika® Stabilizer-1 HC IN can be added with the mixing water or introduced at the end of the mixing process. In general a mixing time of 30 seconds is essential, although the actual mixing time after adding the admixture depends on the individual circumstances and should be determined by trials.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Sika® Stabilizer-1 HC IN must not be used for wet cast concrete as this could result in excessive air entrainment and subsequent loss of strength. Before use suitability test must be performed.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.
620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
West Bengal, India

Contact:
Phone: +91 33 2447 2448
Fax: +91 33 2397 8688
info.india@in.sika.com
www.sika.in



Product Data Sheet
Sika® Stabilizer-1 HC IN
November 2021, Version 01.01
021404021000000169

SikaStabilizer-1HCIN-en-IN-(11-2021)-1-1.pdf