

PRODUCT DATA SHEET

SikaPlast®-5201 NS

HIGH EFFICIENT SUPERPLASTICIZER

DESCRIPTION

SikaPlast®-5201 NS is the latest development of superplasticizer for concrete. It meets the requirements for high range water reducing superplasticizers

USES

SikaPlast®-5201 NS is a unique multipurpose superplasticiser that is particularly suitable for the production of ready mixed concrete. Additionally it provides high water reduction and improved fresh concrete characteristics.

With its outstanding cost / performance SikaPlast®-5201 NS is used for the following:

- A wide range of applications where excellent workability is requested
- Concrete with high water reduction
- High efficient concrete applications

CHARACTERISTICS / ADVANTAGES

SikaPlast®-5201 NS is a powerful superplasticiser based on advanced technology which gives the following advantages:

- Strong water reduction, resulting in high density, high strength and reduced permeability
- Less sensitive against variations in aggregates and / or different cement types
- High efficiency even at low dosage rates
- Extended workability in conjunction with subsequent strength development
- Superior plasticising effect, resulting in improved flow, placing and compaction characteristics
- Reduced shrinkage during curing and reduced creep when hardened

APPROVALS / STANDARDS

Complies with IS 9103-1999, ASTM C494

PRODUCT INFORMATION

| | |
|----------------------------|---|
| Chemical Base | Modified Polycarboxylate |
| Packaging | 255 kg / Bulk supply |
| Appearance / Colour | Light Brown liquid |
| Shelf Life | 12 months from date of production if stored properly in undamaged unopened, original sealed packaging. |
| Storage Conditions | Store in dry condition at temperatures between +10°C and +40°C. Protect from direct sunlight and frost. |
| Density | ~1.08 kg/l at 25°C |
| pH-Value | > 6 |

APPLICATION INFORMATION

| | |
|---------------------------|--|
| Recommended Dosage | 0.5 % to 2.0 b. w. o. c. Optimum dosage has to be finalized through site trials. Stir well before use. |
| Compatibility | SikaPlast®-5201 NS may be combined with many other Sika® products. Compatible with all types of cement and cementitious material. Important: Always conduct trials before combining products in specific mixes and contact our Technical Service Department for information about specific combinations. |

APPLICATION INSTRUCTIONS

DISPENSING

SikaPlast®-5201 NS is added to the gauging water or added with it into the concrete mixer. To take advantage of the high water reduction, a wet mixing time, which is depending on the mixing conditions and mixer performance, of at least 60 seconds is recommended. To avoid excess water in the concrete, the final dosage must begin only after 2/3 of the wet mixing time.

LIMITATIONS

When using SikaPlast®-5201 NS a suitable mix design has to be taken into account and local material sources shall be trialled.

SikaPlast®-5201 NS shall not be added to dry cement. Excessive water addition or overdosing may cause bleeding or segregation.

Frost:

If frozen and / or if precipitation has occurred, SikaPlast®-5201 NS may be used after thawing slowly at room temperature followed by intensive remixing.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.
620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
Tel : +91 33 24472448
Fax : +91 33 23978688
Mail : info.india@in.sika.com



Product Data Sheet
SikaPlast®-5201 NS
October 2016, Version 01.01
021301011000001540

SikaPlast-5201NS-en-IN-(10-2016)-1-1.pdf

