

## PRODUCT DATA SHEET

# Sarnacol®-2170

Contact adhesive for Sarnafil® felt backed roof waterproofing membranes

### DESCRIPTION

Sarnacol®-2170 is a 1-part, nitrile rubber based solvent contact adhesive.

### USES

- Bonding Sarnafil® G-type and Sarnafil® G Felt-type waterproofing membranes to substrates and for perimeter and flashing details.

#### Bonding substrates:

- Concrete, lightweight concrete, brick, plaster
- Oriented strand boards (OSB), plywood panels
- Fibre cement boards
- Mineral fibre boards with sufficient compressive strength and appropriate surface for bonding
- Polyester, hard and soft PVC
- Galvanized steel, PVC-coated metal sheet
- PUR/PIR insulation boards with lamination (glass or mineral fibre fleece)

### CHARACTERISTICS / ADVANTAGES

- Proven performance over decades
- Adheres to solid, rough and clean surfaces
- Application by brush or roller
- Good adhesion to different substrates

### PRODUCT INFORMATION

<b>Chemical base</b>	Solvented nitrile rubber	
<b>Packaging</b>	One way container:	5 kg, 20 kg
	Packing unit:	Euro pallet or single container
<b>Shelf life</b>	24 months from date of production	
<b>Storage conditions</b>	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.	
<b>Density</b>	~0.90 kg/L (+20 °C)	
<b>Consistency</b>	Liquid	
<b>Volatile organic compound (VOC) content</b>	VOC-CH (VOCV)	77 %
	VOC-EU (Solvent)	77 %

## SYSTEM INFORMATION

<b>Compatibility</b>	Shall not be used on substrates: <ul style="list-style-type: none"><li>▪ EPS/XPS insulation boards</li><li>▪ Copper plate</li><li>▪ Bituminous substrates</li><li>▪ Waterproofing membranes (thermoplastics/elastomers) excluding soft PVC</li></ul> These materials could adversely affect the product properties.
----------------------	---

## APPLICATION INFORMATION

<b>Consumption</b>	~300 g/m <sup>2</sup> –500 g/m <sup>2</sup> up to 1000 g/m <sup>2</sup> on very absorbent substrates. Consumption depends on the roughness and absorbency of the substrate. These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.
<b>Ambient air temperature</b>	+5 °C min.
<b>Substrate temperature</b>	+5 °C min.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTS

- Installation instructions and Product Data Sheet of the relevant roof waterproofing membrane.

## IMPORTANT CONSIDERATIONS

- The use of some ancillary products such as adhesives, cleaners and solvents is limited to temperatures above +5 °C. Observe temperature limitations in the appropriate Product Data Sheets.
- Special measures may be compulsory for installation below +5 °C ambient temperature due to safety requirements in accordance with national regulations.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

The substrate must offer sufficient strength and adhesion to resist the forces generated by wind suction.

### SUBSTRATE PREPARATION

The substrate must be resistant to solvents and must be firm, clean, dry, free from oil, grease, dust, stripping agents and loose friable particles. Sheet metal must be cleaned with Sarna Cleaner before adhesive is

applied.

### APPLICATION

Reference must be made to further documentation where applicable, such as relevant method statement, application manual and installation or working instructions.

### General information

Sarnacol®-2170 must be stirred carefully before use. Keep adhesive container closed whenever adhesive is not being used to keep workability constant (to reduce solvent evaporation).

Viscosity of the Sarnacol®-2170 contact adhesive can be changed and adapted by adding Sarna Cleaner. It may be necessary to modify the viscosity after prolonged storage or if container was opened for long periods of time. Mix Sarna Cleaner into the adhesive by carefully stirring small quantities into the adhesive to achieve the desired viscosity.

Use Sarna Cleaner to remove adhesive residue from the roof membrane.

**Contact bonding procedure** (Sarnafil® G-types on substrates and for perimeter / flashing details)

Spread adhesive evenly onto the substrate using an application roller. Do not apply the adhesive to an area greater than can be covered in one day. Allow the adhesive to dry completely. Apply 2 coats of adhesive on absorbent substrates (the first coat must be completely dry before the second is applied).

Apply the adhesive evenly on the underside of the roof membrane (note: welding seam overlap area must be free of adhesive). Once the adhesive has been allowed to evaporate sufficiently (finger test), apply the membrane onto the substrate adhesive. Press down firmly on the membrane using a suitable pressure roller.

At locations which will be exposed to stresses immediately after bonding (edges), Sarnafil® G-types can also be heated externally by means of a heat source (Sarnafil® heat gun) then pressed down immediately using a suitable pressure roller.

#### **Wet bonding procedure** (Sarnafil® G Felt-types on substrates)

Spread adhesive evenly onto the substrate using an application roller. Do not apply the adhesive to an area greater than can be covered in one day. Allow the adhesive to dry completely. Apply a second coat of adhesive over the substrate. Apply the membrane onto the wet substrate adhesive. Press down firmly on the membrane using a suitable pressure roller.

#### **CLEANING OF TOOLS**

Clean all tools and application equipment with Sika® Sarna Cleaner immediately after use. Hardened material can only be mechanically removed.

#### **LOCAL RESTRICTIONS**

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### **Sika India Pvt. Ltd.**

620, Diamond Harbour Road  
Commercial Complex II  
Kolkata - 700 034  
West Bengal, India

#### **Contact:**

Phone: +91 33 2447 2448  
Fax: +91 33 2397 8688  
info.india@in.sika.com  
www.sika.in



#### **Product Data Sheet**

**Sarnacol®-2170**

November 2021, Version 02.01  
020945072000000004

Sarnacol-2170-en-IN-(11-2021)-2-1.pdf