

## PRODUCT DATA SHEET

# SikaPlast®-210 X

High range water reducer / superplasticiser

## **DESCRIPTION**

SikaPlast®-210 X is a concrete superplasticizer based on modified polycarboxylate ether. The Product is used in ready-mix and site-batched concrete for high water reduction combined with high setting control.

## **USES**

SikaPlast®-210 X is used for:

- Economic, eco-friendly and ergonomic production of concrete mixes with highly workable, non-segregating concrete utilizing low water cement ratios
- Ready-mixed concrete
- Pumped concrete
- Long-distance transporting
- High workability without segregation or bleeding
- High durability

## **CHARACTERISTICS / ADVANTAGES**

- High water reduction
- Good dispersion even in mixes with high fines
- High workability for longer periods
- Lowers pumping pressure
- Resistance to segregation even at high workability
- Extended setting with longer workability
- Higher final strengths
- Improves surface appearance and durability of concrete

## **APPROVALS / STANDARDS**

Conforms to IS 9103 / ASTM C494

## PRODUCT INFORMATION

Aqueous solution of modified polycarboxylates
230/255 kg drum/ bulk supply
Light brown liquid
12 months from date of production
The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +40 °C.  Protect from direct sunlight and frost. Always refer to the packaging.  Frost: If frozen or if precipitation has occurred, the Product may be used after thawing slowly at room temperature and intensive mixing.
~1.06 kg/l at 25°C
≥ 6

**Product Data Sheet** 

**SikaPlast®-210 X**February 2025, Version 01.01 021301011000005745

## APPLICATION INFORMATION

#### **Recommended Dosage**

• 0.2% to 2% by weight of cementitious.

The dosage rates given above are for typical usages, they are not meant as absolute limits, as other dosages may be utilized in special cases according to specific job conditions.

Note: Preliminary laboratory trials are always recommended to determine the optimum consumption and injection parameters.

Contact Sika Technical Services for additional information.

#### SYSTEM INFORMATION

#### Compatibility

The Product is compatible with most of the Sika products. Use Sika® Stabilizer as viscosity modifying agent in self compacting concrete

The Product is not compatible with melamine or naphthalene based admixtures.

The Product is compatible with all standard cement types. For use with other cements contact your local Sika technical service for information. The Product can be combined and is recommended for use with other Sika products, such as:

- SikaRapid® hardening accelerators
- Sika® Stabilizer workability improver, for example Sika® Stabilizer VMA series to modify viscosity
- SikaControl® durability and quality enhancer, for example SikaControl®
   AER series to improve frost and thaw resistance
- Sika® Separol® mould release agents
- Sika® Antisol® curing compounds

The Product is not compatible with admixtures from the Sikament® range. Always conduct trials before combining different products. Contact Sika Technical Services for additional information.

## **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## **IMPORTANT CONSIDERATIONS**

When using SikaPlast®-210 X a suitable mix design has to be taken into account and local material sources shall be trialled.

SikaPlast®-210 X shall not be added to dry cement. Excessive water addition, overdosing, changes in aggregates properties, cement properties, cementitious materials properties may cause bleeding, segregation issue, workability or setting issues.

## **ECOLOGY, HEALTH AND SAFETY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

#### **MIXING**

The Product is a ready-to-use liquid that is added to

the concrete during the mixing process. Optimal water reduction is obtained if the Product is dispensed into the concrete mix after the addition of 50–90 % of mixing water. Avoid adding the Product to dry materials. The Product should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing the Product they must be dispensed separately.

After adding the Product allow enough mixing time to secure a homogenous concrete. If necessary, continue mixing and add additional Product to obtain the required workability.

## **LOCAL RESTRICTIONS**

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a

Product Data Sheet SikaPlast®-210 X February 2025, Version 01.01

021301011000005745



particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Sika India Pvt. Ltd.

620, Diamond Harbour Road Commercial Complex II Kolkata - 700 034 West Bengal, India

#### Contact:

Phone: +91 33 2447 2448 Fax: +91 33 2397 8688 info.india@in.sika.com www.sika.in









Product Data Sheet SikaPlast®-210 X February 2025, Version 01.01 021301011000005745



SikaPlast-210X-en-IN-(02-2025)-1-1.pdf