

**BUILDING TRUST** 

PRODUCT DATA SHEET

# SikaPower®-380 AP

Spot welding structural adhesive

# TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	Epoxy-Hybrid
Color (CQP001-1)	Yellow, black
Density (uncured)	1.28 kg/l
Application temperature	20 – 40 °C
Viscosity η* (DIN 54458) 25 °C	600 Pa·s
Curing time at 180 °C	20 minutes
Tensile lap-shear strength (CQP046-9 / ISO 4587)	30 MPa <sup>A</sup>
T-peel strength (CQP580-2, -6 / ISO 11339)	8 N/mm
Tensile strength (CQP580-5, -6 / ISO 527)	26 MPa
Elongation at break (CQP580-5, -6 / ISO 527)	8 %
Glass transition temperature, DMTA (DIN EN ISO 6721)	110 °C
Shelf life	9 months <sup>B</sup>

CQP = Corporate Quality Procedure

 $^{\mbox{\scriptsize A)}}$  adhesive layer: 25 x 12.5 x 0.25 mm / on 1.8 mm SPCC

 $^{\text{B})}$  stored (unopened) in a dry place at  $\leq$  25 °C

# **DESCRIPTION**

SikaPower®-380 AP is a cold applied, structural heat curing adhesive based on epoxy.
SikaPower®-380 AP is designed for sheet metal assembly in the body shop and is cured with heat (e.g. in the e-coat oven).

# PRODUCT BENEFITS

- Spot welding
- High strength
- Adheres well to oily substrates
- High wash out resistance
- Suitable for bonding different metals
- Provides protection against corrosion

# AREAS OF APPLICATION

SikaPower®-380 AP is suitable for high structural bonding of different types of metals. As an adhesive it is designed for use in combination with spot-welding, riveting, clinching and other mechanical fastening techniques, and in some cases as a partial replacement for them. The bonding of oily substrates is possible up to an oil amount of 3 g/m². Due to the wide variety of oils, tests with original substrates and conditions are mandatory.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

## **CURE MECHANISM**

SikaPower®-380 AP is cured by heat. The cure-rate depends on temperature and time of exposure. The most common heat sources are con-vection ovens. The maximum temperature must not exceed 220 °C.

## METHOD OF APPLICATION

#### Application

SikaPower®-380 AP can be processed with manual-, pneumatic- or electric driven piston guns as well as dispensing equipment.

For advice on selecting and setting up a suitable pump system and related process parameters, contact the System Engineering Department of Sika Industry.

## **FURTHER INFORMATION**

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

Safety Data Sheets

# PACKAGING INFORMATION

Cartridge	300 ml
Pail	23 I
Drum	195 I

## **BASIS OF PRODUCT DATA**

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## **HEALTH AND SAFETY INFORMATION**

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

# **DISCLAIMER**

The information, and in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaPower®-380 AP Version 02.01 (07 - 2025), en\_IN 013006303800001000 **Sika India Pvt. Ltd.** Plot No. D102/2, TTC Industrial Area

Navi Mumbai, Darave Thane - 400706 Maharashtra, India Phone: +91 22 6270 4038/4039 info.india@in.sika.com

