

PRODUCT DATA SHEET

Sikament®-119 X

High range water reducer / superplasticiser

DESCRIPTION

Sikament®-119 XPCE based Super-plasticizers is a high range water reducer / superplasticiser for workability retained concrete and mortar.

USES

Sikament®-119 X is used for:

- Economic, eco-friendly and ergonomic production of concrete mixes with highly workable, non-segregating concrete utilizing low water cement ratios
- Ready-mixed concrete
- Long-distance transporting
- Precast concrete
- Pumped concrete

CHARACTERISTICS / ADVANTAGES

- High water reduction
- High workability for longer periods
- Lowers pumping pressure
- High slump retention
- Higher final strengths

APPROVALS / STANDARDS

Conforms to IS 9103/ ASTM C494

PRODUCT INFORMATION

Chemical base	Aqueous solution of Naphthalene
Packaging	275kg drum
Appearance / Colour	Dark brown liquid
Shelf life	12 months from date of production
Storage conditions	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight and frost. Always refer to the packaging. Frost: If frozen or if precipitation has occurred, the Product may be used after thawing slowly at room temperature and intensive mixing.
Density	~1.20 kg/l at 25°C
pH-value	≥ 6

APPLICATION INFORMATION

Recommended Dosage

- 0.2 to 2% by weight of cementitious.

The dosage rates given above are for typical usages, they are not meant as absolute limits, as other dosages may be utilized in special cases according to specific job conditions.

An overdosing may cause:

- Reduced permeability
- Long extension of initial and final set
- Increase in air entrainment

Note: Preliminary laboratory trials are always recommended to determine the optimum consumption and injection parameters.

Contact Sika Technical Services for additional information.

SYSTEM INFORMATION

Compatibility

The Product is compatible with most of the Sika products. Use Sika® Stabilizer as viscosity modifying agent in self compacting concrete.

The Product is compatible with all standard cement types. For use with other cements contact your local Sika technical service for information.

The Product can be combined and is recommended for use with other Sika products, such as:

- SikaRapid® hardening accelerators
- Sika® Stabilizer workability improver
- SikaControl® durability and quality enhancer
- Sika® Separol® mould release agents
- Sika® Antisol® curing compounds

Always conduct trials before combining different products.

Contact Sika Technical Services for additional information.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

MIXING

The Product is a ready-to-use liquid that is added to the concrete during the mixing process. Optimal water reduction is obtained if the Product is dispensed into the concrete mix after the addition of 50–90 % of mixing water. Avoid adding the Product to dry materials. The Product should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing the Product they must be dispensed separately.

After adding the Product allow enough mixing time to secure a homogenous concrete. If necessary, continue mixing and add additional Product to obtain the required workability.

Sika India Pvt. Ltd.

620 Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034

Contact:

Phone: +91 33 2447 2448
Fax: +91 33 2397 8688
info.india@in.sika.com

Note that, as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.



Product Data Sheet

Sikament®-119 X

February 2026, Version 01.01
021302011000246123

Sikament-119X-en-IN-(02-2026)-1-1.pdf