

## PRODUCT DATA SHEET

# SikaWrap®-600 C WV

Woven unidirectional carbon fibre fabric, designed for structural strengthening applications as part of the Sika® strengthening system

### DESCRIPTION

SikaWrap®-600 C WV is a unidirectional woven heavy carbon fibre fabric with mid-range strength, designed for installation using the wet application process.

### USES

SikaWrap®-600 C WV may only be used by experienced professionals.

Structural strengthening of reinforced concrete, masonry, brickwork and timber elements or structures, to increase axial, flexural and shear loading capacity for:

- Improved seismic performance of masonry walls
- Replacing missing steel reinforcement
- Increasing the strength and ductility of columns
- Increasing the loading capacity of structural elements
- Enabling changes in use / alterations and refurbishment
- Correcting structural design and / or construction defects
- Increasing resistance to seismic movement
- Improving service life and durability
- Structural upgrading to comply with current standards

### PRODUCT INFORMATION

<b>Construction</b>	Fibre orientation	0° (unidirectional)	
	Warp	Black carbon fibres 95 %	
	Weft	E-Glass 5 %	
<b>Fibre type</b>	Selected mid-range strength carbon fibres		
<b>Packaging</b>		<b>Fabric length per roll</b>	<b>Fabric width</b>
	1 roll in a cardboard box	≥ 50 m	500 mm
<b>Shelf life</b>	24 months from date of production		

<b>Storage conditions</b>	Store in undamaged, original sealed packaging, in dry conditions at temperatures between +5 °C and +35 °C. Protect from direct sunlight.		
<b>Dry fibre density</b>	1.81 g/cm <sup>3</sup>		
<b>Dry fibre thickness</b>	0.331 mm (based on fibre content)		
<b>Area density</b>	600 g/m <sup>2</sup> ± 20 g/m <sup>2</sup> (carbon fibres only)		
<b>Dry fibre tensile strength</b>	4 000 N/mm <sup>2</sup>		(ISO 10618)
<b>Dry fibre modulus of elasticity in tension</b>	230 000 N/mm <sup>2</sup>		(ISO 10618)
<b>Dry fibre elongation at break</b>	2.1 %		(ISO 10618)

## TECHNICAL INFORMATION

<b>Laminate nominal thickness</b>	0.331 mm		
<b>Laminate nominal cross section</b>	331 mm <sup>2</sup> per m width		
<b>Laminate tensile strength</b>	<b>Average</b>	<b>Characteristic</b>	(EN 2561*)
	3 500 N/mm <sup>2</sup>	3 200 N/mm <sup>2</sup>	(ASTM 3039*)
<b>Laminate modulus of elasticity in tension</b>	<b>Average</b>	<b>Characteristic</b>	(EN 2561*)
	235 kN/mm <sup>2</sup>	200 kN/mm <sup>2</sup>	(ASTM 3039*)
* modification: sample with 50 mm Values in the longitudinal direction of the fibres Single layer, minimum 27 samples per test series			
<b>Laminate elongation at break in tension</b>	1.56 %		(based on EN 2561)
	1.59 %		(based on ASTM 3039)
<b>Tensile resistance</b>	<b>Average</b>	<b>Characteristic</b>	(based on EN 2561)
	1155 N/mm	1056 N/mm	(based on ASTM 3039)
<b>Tensile stiffness</b>	<b>Average</b>	<b>Characteristic</b>	(based on EN 2561)
	74.3 MN/m	72.6 MN/m	
	74.3 kN/m per ‰ elongation	72.6 kN/m per ‰ elongation	
	<b>Average</b>	<b>Characteristic</b>	(based on ASTM 3039)
	72.6 MN/m	69.3 MN/m	
	72.6 kN/m per ‰ elongation	69.3 kN/m per ‰ elongation	

## SYSTEM INFORMATION

<b>System structure</b>	The system build-up and configuration as described must be fully complied with and may not be changed.	
	Concrete substrate adhesive primer	Sikadur®-330 IN
	Impregnating / laminating resin	Sikadur®-300 IN
	Structural strengthening fabric	SikaWrap®-600 C WV
	For detailed information on Sikadur®-330 IN or Sikadur®-300 IN, together with the resin and fabric application details, please refer to the Product Data Sheet of Sikadur®-330 IN and Sikadur®-300 IN and to the relevant Method Statement.	

## APPLICATION INFORMATION

### Consumption

**Wet application with Sikadur®-330 IN as primer and Sikadur®-300 IN as impregnating resin:**

Fabric impregnation	0.4–0.6 kg/m <sup>2</sup>
---------------------	---------------------------

First layer fabric including primer	0.8–1.2 kg/m <sup>2</sup>
-------------------------------------	---------------------------

Following fabric layers	0.5–0.8 kg/m <sup>2</sup>
-------------------------	---------------------------

Note: Consumption is for standard application only. Rough or uneven substrate surfaces, fabrics crossings, loss and wastage can lead to a higher resin consumption.

Please also refer to the relevant Method Statement for further information.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTS

### Method Statements

Ref. 850 41 03: SikaWrap® manual wet application

Ref. 850 41 04: SikaWrap® machine wet application

## IMPORTANT CONSIDERATIONS

- SikaWrap®-600 C WV shall only be applied by trained and experienced professionals.
- A specialist structural engineer must be consulted for any structural strengthening design calculation.
- SikaWrap®-600 C WV fabric is coated to ensure maximum bond and durability with the Sikadur® adhesives / impregnating / laminating resins. To maintain and ensure full system compatibility, do not interchange different system components.
- SikaWrap®-600 C WV can be over coated with a cementitious overlay or other coatings for aesthetic and / or protective purposes. The over coating system selection is dependent on the exposure and the project specific requirements. For additional protection against UV light in exposed areas use Sikagard®-550 W IN, Sikagard®-680 MY or Sikagard® PU UR.
- Please refer to the Method Statement of SikaWrap® manual wet application (Ref. 850 41 03) or SikaWrap® machine wet application (Ref. 850 41 04) for further information, guidelines and limitations.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

Minimum substrate tensile strength: 1.0 N/mm<sup>2</sup> or as specified in the strengthening design.

Please also refer to the relevant Method Statement for further information.

### SUBSTRATE PREPARATION

Concrete must be cleaned and prepared to achieve a laitance and contaminant free, open textured surface. Please also refer to the relevant Method Statement for further information.

### APPLICATION METHOD / TOOLS

The fabric can be cut with special scissors or a Stanley knife (razor knife / box-cutter knife). Never fold the fabric.

SikaWrap®-600 C WV is applied using the wet application process.

Please refer to the relevant Method Statement for details on the impregnating / laminating procedure.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika India Pvt. Ltd.

620, Diamond Harbour Road  
Commercial Complex II  
Kolkata - 700 034  
West Bengal, India

### Contact:

Phone: +91 33 2447 2448  
Fax: +91 33 2397 8688  
info.india@in.sika.com  
www.sika.in



### Product Data Sheet

SikaWrap®-600 C WV  
July 2022, Version 01.01  
020206020010000065

SikaWrap-600CWV-en-IN-(07-2022)-1-1.pdf