

## PRODUCT DATA SHEET

# Sikament® RB 1124

(formerly MasterRheobuild® 1124)

High-range, retarding superplasticiser for high performance concrete mixes

## DESCRIPTION

Sikament® RB 1124 is composed of synthetic polymers specially designed to allow considerable reduction of mixing water while maintaining control on extend of set retardation.

Sikament® RB 1124 is preferred admixture for triple blend binder system based high performance concrete (HPC) mixes or mixes containing micro silica or metakaolin.

Sikament® RB 1124 is chloride free.

## USES

Sikament® RB 1124 is used for:

- Economic, eco-friendly and ergonomic production of concrete mixes with highly workable, non-segregating concrete utilizing low water cement ratios
- Ready-mixed concrete
- Long-distance transporting
- Precast concrete
- Pumped concrete

## PRODUCT INFORMATION

<b>Packaging</b>	275 kg drum
<b>Shelf life</b>	12 months from date of production
<b>Storage conditions</b>	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight and frost. Always refer to the packaging. Frost: If frozen or if precipitation has occurred, the Product may be used after thawing slowly at room temperature and intensive mixing.
<b>Appearance / Colour</b>	Dark brown liquid
<b>Density</b>	1.26 ± 0.02 at 25°C
<b>pH-value</b>	≥ 6

## SYSTEM INFORMATION

---

## Compatibility

The Product is compatible with most of the Sika products. Use Sika® Stabilizer as viscosity modifying agent in self compacting concrete.

The Product is not compatible with melamine or naphthalene based admixtures.

The Product is compatible with all standard cement types. For use with other cements contact your local Sika technical service for information. The Product can be combined and is recommended for use with other Sika products, such as:

- SikaRapid® hardening accelerators
- Sika® Stabilizer workability improver
- SikaControl® durability and quality enhancer
- Sika® Separol® mould release agents
- Sika® Antisol® curing compounds

The Product is not compatible with admixtures from the Sikament® range.

Always conduct trials before combining different products.

Contact Sika Technical Services for additional information.

---

## APPLICATION INFORMATION

---

### Recommended Dosage

Optimum dosage of Sikament® RB 1124 should be determined with trial mixes. As a guide, a dosage range of 500ml to 1500ml per 100kg of cementitious material is normally recommended.

The dosage rates given above are for typical usages, they are not meant as absolute limits, as other dosages may be utilized in special cases according to specific job conditions.

An overdosing may cause:

- Reduced permeability
- Long extension of initial and final set
- Increase in air entrainment

Note: Preliminary laboratory trials are always recommended to determine the optimum consumption and injection parameters.

Contact Sika Technical Services for additional information.

---

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### MIXING

The Product is a ready-to-use liquid that is added to the concrete during the mixing process. Optimal water reduction is obtained if the Product is dispensed into the concrete mix after the addition of 50–90 % of mixing water. Avoid adding the Product to dry materials. The Product should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing the Product they must be dispensed separately.

After adding the Product allow enough mixing time to

secure a homogenous concrete. If necessary, continue mixing and add additional Product to obtain the required workability.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika India Pvt. Ltd.

620, Diamond Harbour Road  
Commercial Complex II  
Kolkata - 700 034  
West Bengal, India

### Contact:

Phone: +91 33 2447 2448  
Fax: +91 33 2397 8688  
info.india@in.sika.com  
www.sika.in



### Product Data Sheet

Sikament® RB 1124

July 2024, Version 01.01  
02130200000002036

SikamentRB1124-en-IN-(07-2024)-1-1.pdf