

PRODUCT DATA SHEET

SikaCor® EG Phosphat Rapid

FAST CURING, HIGH-SOLID EPOXY ZINC PHOSPHATE PRIMER

DESCRIPTION

SikaCor® EG Phosphat Rapid is a fast curing 2-pack primer based on epoxy resin containing zinc phosphate. Low solvent content according to Protective Coatings Directive of German Paint Industry Association (VdL-RL 04).

USES

SikaCor® EG Phosphat Rapid may only be used by experienced professionals. Designed as fast curing primer for steel surfaces exposed to atmospherical conditions. In combination with 2-pack intermediate and top coats SikaCor® EG Phosphat Rapid is a mechanical resistant coating system for rural, urban, industry and sea atmosphere according to ISO 12944-2.

CHARACTERISTICS / ADVANTAGES

- Excellent corrosion protection due to active anticorrosive pigments
- Overcoatable at low temperatures down to - 10 °C
- Fast overcoatable
- Dry film thickness up to 120 µm per layer

APPROVALS / STANDARDS

- Approved according to German standard 'TL/TP-KOR-Stahlbauten', page 97.

PRODUCT INFORMATION

Packaging	SikaCor® EG Phosphat Rapid	28.5 kg net.
	Sika® Thinner EG	25 l, 10 l and 3 l
	SikaCor® Cleaner	160 l and 25 l
Appearance / Colour	Sand yellow approx. RAL 1002, mat.-no. 697.02 Redbrown approx. RAL 8012, mat.-no. 697.06	
Shelf Life	3 years	
Storage Conditions	In originally sealed containers in a cool and dry environment.	
Density	~1.6 kg/l	
Solid Content	~57 % by volume ~79 % by weight	

TECHNICAL INFORMATION

Chemical Resistance	Combined with 2-pack epoxy intermediate coats and 2-pack PUR top coats: Weathering, water, sewage, seawater, smoke, de-icing salts, acid and lye vapours, oils, grease and short term exposure to fuels and solvents.
Thermal Resistance	Dry heat up to + 100°C, short term up to + 150°C In case of higher temperatures please consult Sika.

SYSTEM INFORMATION

Systems	<u>Steel:</u> 1 - 2 x SikaCor® EG Phosphat Rapid Suitable intermediate and top coats: 2-pack top coats of our SikaCor® and Sika® Permacor® range.
----------------	--

APPLICATION INFORMATION

Mixing Ratio		Components A : B	
	By weight	94.7 : 5.3	
	By volume	9.2 : 1	
Thinner	Sika® Thinner EG If necessary max. 5% Sika® Thinner EG may be added to adapt the viscosity.		
Consumption	Theoretical material-consumption/VOC without loss for medium dry film thickness: Dry film thickness <u>80 µm</u> Wet film thickness <u>140 µm</u> Consumption <u>~0.225 kg/m²</u> VOC <u>~47.2 g/m²</u> With SikaCor® EG Phosphat Rapid up to 120 µm dry film thickness per application can be achieved by airless spraying.		
Product Temperature	Min. + 0°C		
Relative Air Humidity	Max. 85 %, except the surface temperature is significantly higher than the dew point temperature, it shall be at least 3 K above dew point. The surface must be dry and free from ice.		
Surface Temperature	Min. - 10°C		
Pot Life	At + 10°C	~8 h	
	At + 20°C	~5 h	
	At + 30°C	~2 h	
Drying Stage 6		Dry film thickness 80 µm	(ISO 9117-5)
	+ 0°C after	10 h	
	+ 5°C after	5 h	
	+ 10°C after	4 h	
	+ 20°C after	1.5 h	
Waiting Time / Overcoating	Min. until drying stage 6 is achieved Max. 1 year In case of longer waiting times please contact Sika. SikaCor® EG Phosphat Rapid cures also at low temperatures below 0 °C. The revision intervals delayed significantly and have to be determined on site. Make sure that all contamination is removed before overcoating with top-coats (see below: surface preparation).		

Drying Time

Final drying time

Depending on film thickness and temperature full hardness is achieved after 1 - 2 weeks. Tests of the completed coating system should only be carried out after final curing.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Steel:

Blast cleaning to Sa 2 ½ according to ISO 12944-4.
Free from dirt, oil and grease.

For contaminated and weathered surfaces we recommend to clean with SikaCor® Wash

MIXING

Stir component A very thoroughly using an electric mixer (start slowly, then increase up to approx. 300 rpm). Add component B carefully and mix both components very thoroughly (including sides and bottom of the container). Mix for at least 3 minutes until a homogeneous mixture is achieved. Fill mixed material into clean container and mix again shortly as described above. During mixing and handling of the materials always wear protective goggles, suitable gloves and other protective clothings.

APPLICATION

The method of application has a major effect on achieving uniform thickness and appearance. Spray application will give the best results. The indicated dry film thickness is easily achieved by airless spray. Adding solvents reduces the sag resistance and the dry film thickness. In case of application by roller or brush, additional applications may become necessary to achieve the required coating thickness, depending on type of construction, site conditions, colour shade etc. Prior to major coating operations a test application on site may be useful to ensure the selected application method will provide the requested results.

By brush and roller

Conventional high pressure spraying:

- Nozzle size 1.5 - 2.5 mm
- Pressure 3 - 5 bar
- Oil and water trap is compulsory

Airless-spraying:

- Pressure min. 180 bar
- Nozzle size 0.38 - 0.53 mm (0.015 - 0.021 inch)
- Spraying angle 40° - 80°

CLEANING OF TOOLS

SikaCor® Cleaner

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

GISCODE: RE 3

This coding enables additional information and help with the creation of operating instructions (WINGIS online) to be obtained on the BG Bau service pages (www.gisbau.de).

Skin contact with epoxy resins can lead to allergies!

Avoid direct skin contact at all costs when handling epoxy resins!

For the selection of suitable protective equipment, we have made our information data sheets 7510 'General notes on occupational safety' and 7511 'General notes for wearing protective gloves' available at www.sika.de. In conjunction with this we also recommend the BG Bau service pages for information regarding the handling of epoxy resins (www.bgbau.de/gisbau/fachthemen/epoxi).

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU Directive 2004/42/CE, the maximum allowed content of VOC (product category IIA / j type Sb) is 500 g/l (Limits 2010) for the ready to use product.

The maximum content of SikaCor® EG Phosphat Rapid is < 500 g/l VOC for the ready to use product.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability

for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.
620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
Tel : +91 33 24472448
Fax : +91 33 23978688
Mail : info.india@in.sika.com



Product Data Sheet
SikaCor® EG Phosphat Rapid
December 2018, Version 03.01
020602000040000007

SikaCorEGPhosphatRapid-en-IN-(12-2018)-3-1.pdf

