

PRODUCT DATA SHEET

Sikagard®-5310 Coal Tar

Heavy duty coal tar based epoxy protective coating for concrete

DESCRIPTION

Sikagard®-5310 Coal Tar is a two part reaction hardening, chemical resistant coating based on coal tar epoxy resin, in combination with mineral fillers.

USES

Sikagard®-5310 Coal Tar is used as a protective chemical resistant coating for concrete, as internal and external coating for buried and submerged structures in wastewater, seawater or highly aggressive soils such as:

- Sewage, effluent or waste treatment plants
- Immersed piers
- Concrete silos
- Ship hulls, pipelines, cooling towers
- Oil catchment tanks, pipes and piles of off-shore platforms
- Structures immersed in fresh and salt water
- Chemical storages
- Marine structures

Sikagard®-5310 Coal Tar is **not suitable** for surfaces in contact with drinking water.

CHARACTERISTICS / ADVANTAGES

- Tough hard, heavy duty
- Abrasion and impact resistant
- Excellent resistance to water and chemicals
- Resistant to microbes

PRODUCT INFORMATION

Product declaration	Confirms to IS 14948 : 2001	
Chemical base	Epoxy resin modified with coal tar	
Packaging	Part A+B pre-batched	5.0 kg
	Part A	0.8 kg container
	Part B	4.2 kg container
Shelf life	12 months from date of production	
Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +35 °C.	

Appearance / Colour	Part A+B	Black liquid
	Part A	Light yellow liquid
	Part B	Black liquid
Density	~1.65 kg/L (Part A+B mixed, +30 °C)	(EN ISO 2811-1)
Flash point	> 30 °C	(ASTM D93)
Solid content by weight	~85 %	
Solid content by volume	~75 %	(IS 101 Part 8/Sec 6)

TECHNICAL INFORMATION

Shore A hardness	~90	(ASTM D2240)			
Resistance to impact	No signs of cracking, flaking or detachment from the panel or loss of adhesion between coats when tested on abrasive blasted panel (7 days, 2 m height) (IS 101 Part 5/Sec 3)				
Tensile adhesion strength	Substrate	Tensile adhesion strength	(EN 1542)		
	Concrete (primed with Sikagard®-5310 Coal Tar diluted with 10 % Sika® Thinner DS)	~2.0 N/mm ²			
	Steel (primed with Sika® FerroGard®-950 IN)	~1.5 N/mm ²			
Chemical resistance	Chemicals	24 hours	3 days	7 days	(IS 4631-1968)
	Sea water	A	A	A	
	Water	A	A	A	
	Nitric acid 1 %	A	D	D	
	Hydrochloric acid 1 %	A	D	D	
	Sulphuric acid 1 %	A	D	D	
	Diesel	A	A	A	
	NaOH 1 %	A	A	A	
A = resistant, D = resistant but with discolouration and/or loss of gloss, C = not resistant Test temperature: +30 °C					

SYSTEM INFORMATION

System structure	Layer	Product
	Primer	1 × Sikagard®-5310 Coal Tar + 10 % dilution with Sika® Thinner DS
	Seal coat	1–2 × Sikagard®-5310 Coal Tar
Dry film thickness	~125 microns per coat	

APPLICATION INFORMATION

Mixing ratio	Part A : Part B = 16 : 84 (by weight)
---------------------	---------------------------------------

Consumption	Layer	Product	Consumption
	Primer	1 × Sikagard®-5310 Coal Tar + 10 % Sika® Thinner DS	~0.15–0.20 kg/m ²
Seal coat	1–2 × Sikagard®-5310 Coal Tar	~0.20–0.30 kg/m ² per coat	
These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level and wastage etc.			
Ambient air temperature	Maximum	+30 °C	
	Minimum	+10 °C	
Relative air humidity	Maximum	75 %	
Dew point	Beware of condensation. The substrate must be at least +3 °C above the dew point to reduce the risk of condensation, which may lead to adhesion failure of final finish. Be aware that the substrate temperature may be lower than the ambient temperature.		
Substrate temperature	Maximum	+30 °C	
	Minimum	+10 °C	
Substrate moisture content	≤ 4 % Test method: Sika®-Tramex meter, CM - measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).		
Pot life	~2 hours at +30 °C		
Curing time	Full cure in ~7 days at +30 °C Note: Times are approximate and will be affected by changing ambient conditions.		
Gel time	~24 hours max.		
Waiting time / Overcoating	Substrate temperature	Minimum	Maximum
	+10 °C	16 hours	7 days
	+20 °C	8 hours	7 days
	+30 °C	4 hours	7 days
Note: The waiting times between applications depend largely on temperature and weather. Lower temperature will increase the minimum and the maximum time specified. To ensure good intercoat adhesion, light grinding of the previous coat followed by a thorough de-dusting is required.			
Drying time	Surface dry	~1.5 h	(IS 101 Part 3/Sec 1)
	Hard dry	~12 h	

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

IMPORTANT

Sikagard®-5310 Coal Tar is not recommended to apply in confined area without proper ventilation & safety equipment. If any customer wants to apply this coating under this type of environment, then customer has to get the clearance from own health and safety department. Applicator has to wear proper safety uniform and must use oxygen cylinder with proper breathing attachment before entering into that area. Avoid staying for longer time during application, must take rest at interval. Whole application has to be done under EHS officer supervision.

APPLICATION INSTRUCTIONS

EQUIPMENT

Mixing

Low speed electric single paddle mixer (300–400 rpm) or other suitable equipment.

Application

- Brush application: Distemper brushes, round brushes or radiator brushes
- Roller application: Short pile lamb skin roller

SUBSTRATE QUALITY

- The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².
- The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. If in doubt apply a test area first.
- Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed.
- The concrete or screed substrate has to be primed or levelled in order to achieve an even surface.

SUBSTRATE PREPARATION

- Concrete substrates must be prepared mechanically using grinding, wire-brushing, abrading, scarifying or preferably by high pressure water/sand blasting equipment to remove cement laitance and achieve an open textured surface.
- Weak concrete must be removed and surface defects such as blow holes, cavities, pinholes and voids must be fully exposed.
- Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor®, Sikadur® and Sikagard® range of materials. High spots can be removed by grinding.
- All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

MIXING

1. Stir Part B thoroughly to remix any settled part.
2. Add Part A and mix thoroughly with an electric single paddle mixer for 3 minutes until a uniform mix has been achieved.

APPLICATION

IMPORTANT

Do not apply Sikagard®-5310 Coal Tar on substrates with rising moisture.

IMPORTANT

Freshly applied must be protected from damp, condensation and water for at least 24 hours.

1. Apply to concrete or steel surface using airless spray, conventional spray, brush and/or roller. A minimum of 2 coats must be applied.

CLEANING OF TOOLS

Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened or cured material can only be mechanically removed.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.

620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
West Bengal, India

Contact:

Phone: +91 33 2447 2448
Fax: +91 33 2397 8688
info.india@in.sika.com
www.sika.in



Product Data Sheet

Sikagard®-5310 Coal Tar

September 2023, Version 01.01
020303120020000025

Sikagard-5310CoalTar-en-IN-(09-2023)-1-1.pdf