

# PRODUCT DATA SHEET

## Sika® ViscoCrete®-5106 ES

### HIGH PERFORMANCE SUPERPLASTICIZING ADMIXTURE

#### DESCRIPTION

Imparts very high workability, improved workability retention, allows a large reduction in water content and helps in development of high early strength.

#### USES

Sika® ViscoCrete®-5106 ES a superplasticizer for free flowing concrete in floors, slabs, foundations, slender components with dense re inforcement, walls and columns and other structural elements.

Sika® ViscoCrete®-5106 ES is mainly used for the following types of concrete:

- High performance concrete
- High Early strength concrete
- Ready mixed concrete
- Self compacting concrete
- Precast concrete
- Pre stressed concrete
- Pumped concrete

#### CHARACTERISTICS / ADVANTAGES

Sika® ViscoCrete®-5106 ES produces a more uniformly cohesive high quality free flowing concrete

Sika® ViscoCrete®-5106 ES will result in the following advantages of concrete:

- Improved dispersion properties
- Very high water reduction
- Very High Early strength
- Improved durability
- Improved cohesion properties
- Improved rheology
- Improved flowability
- Reduced drying shrinkage
- Improved workability retention

#### APPROVALS / STANDARDS

IS 9103, ASTM C494

#### PRODUCT INFORMATION

<b>Chemical Base</b>	Aqueous solution of modified poly carboxylate
<b>Packaging</b>	255 kg drums /Bulk supply
<b>Appearance / Colour</b>	Light Brown Liquid
<b>Shelf Life</b>	12 months from date of production if stored properly in undamaged unopened, original sealed packaging.
<b>Storage Conditions</b>	Store in dry conditions at temperatures between +10°C and +40°C. Protect from direct sunlight and frost.
<b>Density</b>	~1.13 kg/l at 25°C
<b>pH-Value</b>	≥ 6

## APPLICATION INFORMATION

<b>Recommended Dosage</b>	Optimum dosage of Sika® ViscoCrete®-5106 ES should be determined by site trials. Recommended dosage: 0.2 – 2.0% by weight of cementitious. A higher dosage might be used if agreed by client or consultant.
<b>Compatibility</b>	Sika® ViscoCrete®-5106 ES may be combined with many other Sika® Products. Important: Always conduct trials before combining products in specific mixes and contact our Technical Service Department for information about specific combinations. Compatible with all types of cement and cementitious materials.

## APPLICATION INSTRUCTIONS

### DISPENSING

Sika® ViscoCrete®-5106 ES can be added into the mixing water or directly into the concrete mixer after 50 – 70% of the mixing water has been added. The addition of Sika® ViscoCrete®-5106 ES to dry aggregate or cement is not recommended. To achieve optimum performance a minimum wet mixing time, which is depending on the mixing conditions and the mixer performance, of 60 seconds is recommended.

### FURTHER DOCUMENTS

Excessive water addition or overdosing may cause bleeding or segregation. If frozen and / or if precipitation has occurred, Sika® ViscoCrete®-5106 ES may be used after thawing slowly at room temperature and after intensive mixing.

### BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

### ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

### LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika India Pvt. Ltd.**  
620, Diamond Harbour Road  
Commercial Complex II  
Kolkata - 700 034  
Tel : +91 33 24472448  
Fax : +91 33 23978688  
Mail : info.india@in.sika.com



Product Data Sheet  
Sika® ViscoCrete®-5106 ES  
November 2018, Version 01.01  
021301011000001544

SikaViscoCrete-5106ES-en-IN-(11-2018)-1-1.pdf