

## PRODUCT DATA SHEET

## Sikaflex®-258

Primerless windscreen adhesive

## TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	1-component polyurethane
Color (CQP001-1)	Black
Cure mechanism	Moisture-curing
Density (uncured)	1.31 kg/l
Non-sag properties (CQP061-1)	Good
Application temperature	ambient, product 5 – 40 °C
Skin time (CQP019-1)	40 minutes <sup>A</sup>
Open time (CQP526-1)	30 minutes <sup>A</sup>
Curing speed (CQP049-1)	(see diagram)
Shore A hardness (CQP023-1 / ISO 48-4)	50
Tensile strength (CQP036-1 / ISO 527)	4.5 MPa
Elongation at break (CQP036-1 / ISO 527)	450 %
Tensile lap-shear strength (CQP046-1 / ISO 4587)	3.0 MPa
Minimum Drive Away Time (cars) according FMVSS 212 (CQP511-1)	with airbags 3 hours <sup>A, B</sup>
Shelf life (CQP016-1)	9 months <sup>C</sup>

CQP = Corporate Quality Procedure

<sup>A)</sup> 23 °C / 50 % r. h.<sup>B)</sup> details about MDAT contact Sika<sup>C)</sup> stored (unopened) in a dry place at ≤ 25 °C

## DESCRIPTION

Sikaflex®-258 is a cold applied, primerless to glass windshield adhesive, optimized for manual application. It provides a long open time and ensures safe application even under warm conditions.

Note: Primerless to glass application requires the glass to be prepared using an Automotive grade glass cleaner such as Sika® Cleaner G+P. The bonding surfaces must be free of contamination and have proper UV protection.

## PRODUCT BENEFITS

- Solvent free, no odor
- Easy to extrude with manual application gun
- Primerless to glass adhesion
- Good bead stability and non-sag properties
- Short cut-off string

## AREAS OF APPLICATION

Sikaflex®-258 is suitable for experienced professional users only.

This product and related process information is designed for Automotive Glass Replacement. For other applications, tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

## CURE MECHANISM

Sikaflex®-258 cures by reaction with atmospheric moisture. At low temperatures the water content of the air is generally lower and the curing reaction proceeds somewhat slower (see diagram 1).




Diagram 1: Curing speed Sikaflex®-258

## CHEMICAL RESISTANCE

Sikaflex®-258 is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

## METHOD OF APPLICATION

### Surface preparation

Surfaces must be clean, dry and free from grease, oil, dust and contaminants.

The bond faces must be prepared with an Automotive grade glass cleaner such as Sika® Cleaner G+P. Sikaflex®-258 is capable to bond on glass and ceramic frits without additional pre-treatment. It is compatible with Sika's Black-Primerless or All Black installation process.

Glass without ceramic coatings need proper UV protection.

## Application

Sikaflex®-258 can be processed between 5 °C and 40 °C but changes in reactivity and application properties have to be considered. The optimum temperature for substrate and adhesive is between 15 °C and 25 °C.

It is recommended to apply the adhesive with a piston-type application gun.

Consider that the viscosity will increase at low temperature. For easy application, condition the adhesive at ambient temperature prior to use.

To ensure a uniform thickness of the bondline it is recommend to apply the adhesive in form of a triangular bead (see figure 1).




Figure 1: Recommended bead configuration

The open time is significantly shorter in hot and humid climate. The glass must always be installed within the open time. Never install a glass after the product has built a skin.

## Removal

Uncured Sikaflex®-258 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- Black-Primerless installation process chart
- All Black installation process chart

## PACKAGING INFORMATION

Cartridge	310 ml
Unipack	400 ml
	600 ml

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

## DISCLAIMER

The information, and in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

## PRODUCT DATA SHEET

Sikaflex®-258  
Version 03.01 (07 - 2025), en\_IN  
012001212580001000

Sika India Pvt. Ltd.  
Plot No. D102/2, TTC Industrial Area  
Navi Mumbai, Darave  
Thane - 400706  
Maharashtra, India  
Phone: +91 22 6270 4038/4039  
info.india@in.sika.com

