

PRODUCT DATA SHEET

Sikament[®] RB 610

(formerly MasterRheobuild[®] 610)

High range water reducing, superplasticiser for rheoplastic concretes

DESCRIPTION

Sikament[®] RB 610 is a high range water reducer / superplasticiser for workability retained concrete and mortar.

USES

Sikament[®] RB 610 is used for:

- Economic, eco-friendly and ergonomic production of concrete mixes with highly workable, non-segregating concrete utilizing low water cement ratios
- Ready-mixed concrete
- Long-distance transporting
- Mass concrete
- Shotcrete
- Pumped concrete

CHARACTERISTICS / ADVANTAGES

- High water reduction
- High workability for longer periods
- Lowers pumping pressure
- High slump retention
- Higher final strengths

APPROVALS / STANDARDS

Conforms to IS 9103 / ASTM C494 Type D,F,G

PRODUCT INFORMATION

Packaging	235kg drum
Shelf life	12 months from date of production
Storage conditions	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight and frost. Always refer to the packaging. Frost: If frozen or if precipitation has occurred, the Product may be used after thawing slowly at room temperature and intensive mixing.
Appearance / Colour	Dark brown liquid
Density	: 1.09 ± 0.02 at 25°C
pH-value	≥ 6

TECHNICAL INFORMATION

Concreting Guidance	<ul style="list-style-type: none">▪ Follow the standard rules of good concreting practice for both production and placement.▪ Carry out laboratory trials before concreting on site, especially when us-
----------------------------	---

ing a new mix design or producing new concrete components.

- Carry out trials to confirm the flowability and workability of the concrete.
- Cure fresh concrete properly and apply curing as early as possible, particularly in hot, windy and dry conditions, as well as at low temperatures.

Specific Advice

- Excessive water addition or overdosing may cause bleeding, segregation and extension of setting-times.
- Due allowance should be made for the effect of fluid concrete pressure on formwork, and stripping times should be monitored.
- The product ensures that the concrete remains workable for a certain period. Workability loss depends on the following aspects:
 - temperature,
 - type of cement,
 - nature of aggregates,
 - method of transport,
 - and initial workability.
- To achieve longer workability period please use a setting retarder from the Sika® Retarder series.

SYSTEM INFORMATION

Compatibility

The Product is compatible with most of the Sika products.
The Product is compatible with all standard cement types. For use with other cements contact your local Sika technical service for information.
The Product can be combined and is recommended for use with other Sika products, such as:

- SikaRapid® hardening accelerators
- Sika® Stabilizer workability improver
- SikaControl® durability and quality enhancer
- Sika® Separol® mould release agents
- Sika® Antisol® curing compounds

Always conduct trials before combining different products.
Contact Sika Technical Services for additional information.

APPLICATION INFORMATION

Recommended Dosage

200 ml to 1300 ml per 100kg of cementitious material is recommended.
The dosage rates given above are for typical usages, they are not meant as absolute limits, as other dosages may be utilized in special cases according to specific job conditions.
An overdosing may cause:

- Reduced permeability
- Long extension of initial and final set
- Increase in air entrainment

Note: Preliminary laboratory trials are always recommended to determine the optimum consumption and injection parameters.
Contact Sika Technical Services for additional information.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

MIXING

The Product is a ready-to-use liquid that is added to the concrete during the mixing process. Optimal water reduction is obtained if the Product is dispensed into the concrete mix after the addition of 50–90 % of mixing water. Avoid adding the Product to dry materials. The Product should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing the Product they must be dispensed separately.
After adding the Product allow enough mixing time to

secure a homogenous concrete. If necessary, continue mixing and add additional Product to obtain the required workability.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.
620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
West Bengal, India

Contact:
Phone: +91 33 2447 2448
Fax: +91 33 2397 8688
info.india@in.sika.com
www.sika.in



SikamentRB610-en-IN-(07-2024)-1-1.pdf

Product Data Sheet
Sikament® RB 610
July 2024, Version 01.01
02130200000002153