

PRODUCT DATA SHEET

Sika® ViscoCrete® SKY 8605

(formerly MasterGlenium® SKY 8605)

High-performance super plasticiser based on PCE (polycarboxylic ether) for concrete

DESCRIPTION

Sika® ViscoCrete® SKY 8605 is an admixture of a new generation based on modified polycarboxylic ether. The product has been primarily developed for applications in high performance concrete where the highest durability and performance is required. Sika® ViscoCrete® SKY 8605 is free of chloride & low alkali. It is compatible with all types of cements.

USES

- Production of smart dynamic concrete & self-consolidation concrete.
- High performance concrete for durability
- High workability without segregation or bleeding
- Precast & Pre-stressed concrete
- Concrete containing pozzolans such as microsilica, GGBFS, PFA including high volume fly ash concrete

PRODUCT INFORMATION

Packaging	245kg drum
Shelf life	12months from date of production
Storage conditions	Sika® ViscoCrete® SKY 8605 must be stored where temperatures do not drop below +5°C. If product has frozen, thaw at +5°C or above and completely reconstitute using mild mechanical agitation. Do not use pressurized air for agitation. Store under cover, out of direct sunlight and protect from extremes of temperature.
Appearance / Colour	Light to dark reddish brown liquid
Density	1.08 ± 0.02 at 25°C
pH-value	≥ 6

APPLICATION INFORMATION

Recommended Dosage Optimum dosage of Sika® ViscoCrete® SKY 8605 should be determined

CHARACTERISTICS / ADVANTAGES

- Elimination of vibration and reduced labour cost in placing
- Marked increase in early & ultimate strengths
- Improved adhesion to reinforcing and stressing steel
- lower permeability - increased durability

APPROVALS / STANDARDS

IS 9103, ASTM C494 Type F,G

with trial mixes. As a guide, a dosage range of 300ml to 1200ml per 100kg of cementitious material is normally recommended. Because of variations in concrete materials, job site conditions, and/or applications, dosages outside of the recommended range may be required. In such cases, contact your local Sika representative.

For addition information on Sika® ViscoCrete® SKY 8605 admixture or on its use in developing concrete mixes with special performance characteristics, contact your local Sika representative.

Dispensing

Sika® ViscoCrete® SKY 8605 is a ready-to-use liquid which is dispensed into the concrete together with the mixing water. The plasticising effect and water reduction are higher if the admixture is added to the damp concrete after 50 to 70% of the mixing water has been added. The addition of Sika® ViscoCrete® SKY 8605 to dry aggregate or cement is not recommended. Thorough mixing is essential and a minimum mixing cycle, after the addition of the Sika® ViscoCrete® SKY 8605, of 60 seconds for forced action mixers is recommended.

Compatibility

Sika® ViscoCrete® SKY 8605 is compatible with most of the Sika products. It must not be used in conjunction with any other admixture unless prior approval is received from Local Sika Technical Services Department.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.

620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
West Bengal, India

Contact:

Phone: +91 33 2447 2448
Fax: +91 33 2397 8688
info.india@in.sika.com
www.sika.in

**Product Data Sheet**

Sika® ViscoCrete® SKY 8605
July 2024, Version 01.01
021301011000005426

SikaViscoCreteSKY8605-en-IN-(07-2024)-1-1.pdf

