

PRODUCT DATA SHEET

Sikament® RB 1127

(formerly MasterRheobuild® 1127)

High-range, retarding superplasticiser for high performance concrete mixes

DESCRIPTION

Sikament® RB 1127 is composed of synthetic polymers specially designed to allow considerable reduction of mixing water while maintaining control on extend of set retardation.

Sikament® RB 1127 is preferred admixture for triple blend binder system based high performance concrete (HPC) mixes or mixes containing micro silica or metakaolin.

Sikament® RB 1127 is chloride free.

USES

- Concrete containing Silica fume/ Metakaolin
- Ready mixed concrete
- Congested/complex reinforced sections
- Pre-cast concrete production
- Long-distance transporting
- Pumped concrete
- Low water/binder ratio mixes
- Mixes requiring >20% water reductions

PRODUCT INFORMATION

Packaging	275kg
Shelf life	12 months from date of production if stored properly in undamaged un-opened, original sealed packaging.
Storage conditions	Sikament® RB 1127 must be stored where temperatures do not drop below +5°C. If product has frozen, thaw at +5°C or above and completely re-constitute using mild mechanical agitation. Do not use pressurized air for agitation. Store under cover, out of direct sunlight and protect from extremes of temperature. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult your local Sika representative.
Appearance / Colour	Dark brown free flowing liquid

CHARACTERISTICS / ADVANTAGES

- Good dispersion even in mixes with high fines
- Reduced thermal peaks
- High workability for longer periods
- Lower pumping pressure
- Resistance to segregation even at high workability
- Extended setting with longer workability
- Reduced water content for a given workability
- Higher ultimate strengths
- Reduced permeability
- Improved durability
- Reduced shrinkage and creep
- Increased ease in finishing concrete

APPROVALS / STANDARDS

IS 9103, ASTM C-494 Type G, EN 934-2: T11.1/11.2

Density 1.24 ± 0.02 at 25°C

pH-value ≥ 6

APPLICATION INFORMATION

Recommended Dosage

Optimum dosage of Sikament® RB 1127 should be determined with trial mixes. As a guide, a dosage range of 600ml to 1800ml per 100kg of cementitious material is normally recommended. Because of variations in concrete materials, job site conditions, and/or applications, dosages outside of the recommended range may be required. In such cases, contact your local Sika representative.

For addition information on Sikament® RB 1127 admixture or on its use in developing concrete mixes with special performance characteristics, contact your local Sika representative.

Effects of over dosage

A severe over-dosage of Sikament® RB 1127 can result in the following:

- Long extension of initial and final set
- Increase in air entrainment
- Bleed/segregation of mix
- Increased plastic shrinkage

A slight overdosing may not adversely affect the ultimate strength of the concrete and can achieve higher strengths than normal concrete, provided it is properly compacted and cured. Due allowance should be made for the effect of fluid concrete pressure on form work, and stripping times should be monitored.

In the event of over dosage, consult your local Sika representative immediately.

Dispensing

Sikament® RB 1127 is a ready-to-use liquid which is dispensed into the concrete together with the mixing water. The plasticising effect and water reduction are higher if the admixture is added to the damp concrete after 50 to 70% of the mixing water has been added. The addition of Sikament® RB 1127 to dry aggregate or cement is not recommended.

Compatibility

Sikament® RB 1127 is compatible with most admixtures used in the production of quality concrete including normal, other mid-range and high-range water-reducing admixtures, air entrainers, accelerators, retarders, extended set-control admixtures, corrosion inhibitors, and shrinkage reducers.

Sikament® RB 1127 is also compatible with slag and pozzolans such as fly ash, metakaolin and silica fume.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

CORROSIVITY – NON CORROSIVE

Sikament® RB 1127 admixture will neither initiate nor promote corrosion of reinforcing steel embedded in concrete, prestressed concrete or concrete placed on galvanized steel floor and roof systems. Neither calcium chloride nor any calcium chloride-based ingredients are used in the manufacture of Sikament® RB 1127 admixture. In all concrete application, Sikament® RB 1127 admixture will conform to the most stringent or minimum chloride ion limits currently suggested by construction industry standards and practices.

WORKABILITY

Sikament® RB 1127 ensures that rheoplastic concrete remains workable in excess of 45 minutes at +25°C.

Workability loss is dependent on temperature, and on the type of cement, the nature of aggregates, the method of transport and initial workability. It is strongly recommended that concrete should be properly cured particularly in hot, windy and dry climates.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product

may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.

620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
West Bengal, India

Contact:

Phone: +91 33 2447 2448
Fax: +91 33 2397 8688
info.india@in.sika.com
www.sika.in



Product Data Sheet

Sikament® RB 1127

April 2024, Version 01.01
021302011000001277

SikamentRB1127-en-IN-(04-2024)-1-1.pdf