

## PRODUCT DATA SHEET

# Sika® FloorJoint EX A

“Phoenix” Panel prefabricated polymer composite for wide gap eccentric floor joint

### DESCRIPTION

Sika® FloorJoint EX A is a prefabricated, glass-carbon fiber reinforced, extremely resistant, flat and hardly recognizable polymer composite panel with high physical properties. Because of the waved and eccentric joint design an improved load distribution and water proof performance is achieved.

### USES

- Floor joint panel for new build and refurbishment of joints for concrete screeds with normal up to medium heavy wear e.g. for storage and assembly halls, maintenance workshops, hospitals, schools and ware houses.
- Particularly used in the food and pharmaceutical industries, for show rooms, workshops and production areas etc.

### CHARACTERISTICS / ADVANTAGES

- Multiple sandable
- Suitable for heaviest loads
- Rapid implementation for driving on after 24 hours
- No unevenness, ultra-flat
- No vibration while driving
- Allows horizontal movements
- Expansion coefficient similar to resin floors
- Tight coating possible
- Low installation height
- Simple installation
- High chemical resistance
- Suitable for food products
- Temperature and weather resistance
- Partial quick repair possible
- Metal-free, therefore non-corrosive

### APPROVALS / STANDARDS

- Reaction to fire classification acc. to DIN EN 13301-1.
- Test report No.: KB-Hoch-140803.
- The fire behaviour of the polymeric material of Sika® FloorJoint EX A is classified as: Bfl-s1.

### PRODUCT INFORMATION

Chemical base	PUR
Packaging	111 pieces on an EU-pallet weight, approx. ~8.35kg/PCS
Shelf life	3 years
Storage conditions	In cool and dry conditions at temperatures between +5 °C and +30 °C, always in horizontal and flat position.
Appearance / Colour	Grey, approx. RAL 7037
Dimensions	Length × width × height = approx. 1200 mm × 255 mm × 15 mm

## TECHNICAL INFORMATION

Compressive strength	~110 N/mm <sup>2</sup> (14 days, 23 °C / 50 % R.H)	(DIN EN 196-1)
Tensile strength	~50 N/mm <sup>2</sup> (14 days, 23 °C / 50 % R.H)	(DIN EN 196-1)

## APPLICATION INFORMATION

Consumption	1 piece for 1.2 linear meter
Ambient air temperature	+10 °C min. / +30 °C max.
Relative air humidity	80 % max.
Dew point	Beware of condensation! The substrate and uncured floor must be at least +3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.
Substrate temperature	+10 °C min. / +30 °C max. The substrate and uncured floor must be at least +3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.
Substrate moisture content	< 4 % pbw moisture content. Test method: Sika®-Tramex meter, CM - measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATIONS

- This eccentric joint profile must be installed 85 mm offset (eccentric) from the edge of the existing joint. Please refer to Sika Drawings.
- To avoid the risk of crack occurring on the panel surface after a certain time, cut a joint of 20 mm deep and at least 5 mm wide in the end of floorjoint that will isolate the effect of ground movement.
- The Product must only be applied in accordance with its intended use, do remember indoor use only.
- Never remove the masking tape affixed to the bottom side of the Sika® FloorJoint EX A panel. The masking tape is necessary to keep the two composite parts of the panel separate, allowing the movement of the joint after installation.
- No relative vertical displacement of the concrete slabs can occur along the length of either side of the joint. Where necessary, apply appropriate measures such as anchoring/bolting or ground consolidation by injection prior to installation of the Sika® FloorJoint EX A panel.
- Do not exceed the maximum positive joint movement capacity, otherwise the teeth of the panel become unsupported and may break.
- Settlement of the substrate or of the adhesive can result in cracks in Sika® FloorJoint EX A. These cracks do not constitute a defect, since they do not affect the viability and suitability for use.
- Do not exceed the maximum grinding depth of 2 mm. If after grinding the letters on the top surface of

Sika® FloorJoint EX A are no longer visible, the maximum grinding depth of 2 mm has been exceeded and the mechanical resistance of the profile is reduced. Replace the panel if the maximum grinding depth has been exceeded.

- The sealant may break at a positive joint movement of ~10–15 mm, however this does not affect the technical performance of Sika® FloorJoint EX A. The purpose of the joint sealant is the reduction of dirt pick-up in the joint, not to provide water tightness. Install Sikadur-Combiflex® SG System below Sika® FloorJoint EX A if a waterproof joint design is required.
- Periodically inspect the joint sealing material and renew if necessary.
- Do not use a hammer for placing and adjusting the floor panel during installation.

## ECOLOGY, HEALTH AND SAFETY

Ensure proper ventilation and use nose mask during cutting of Sika® FloorJoint EX A panel. Good quality industrial vacuum cleaner is recommended for cleaning the area after cutting.

## REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w).

## APPLICATION INSTRUCTIONS

### APPLICATION

Please refer to the product data sheet of Sikadur®-31 IN and/or the Method Statement "Sika® FloorJoint EX A".

### CLEANING OF TOOLS

Please refer to the product data sheet of Sikadur®-31 IN.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika India Pvt. Ltd.**  
620, Diamond Harbour Road  
Commercial Complex II  
Kolkata - 700 034  
West Bengal, India

**Contact:**  
Phone: +91 33 2447 2448  
Fax: +91 33 2397 8688  
info.india@in.sika.com  
www.sika.in



**Product Data Sheet**  
Sika® FloorJoint EX A  
June 2023, Version 02.02  
020816140020000008

SikaFloorJointEXA-en-IN-(06-2023)-2-2.pdf

