

# PRODUCT DATA SHEET

## Sikament<sup>®</sup> NN

### HIGH RANGE WATER REDUCER / SUPERPLASTICIZING ADMIXTURE FOR CONCRETE

#### DESCRIPTION

A highly effective dual action liquid superplasticiser for the production of high slump concrete or as a substantial water reducing agent.

#### USES

- Slabs and foundations
- Walls, columns and piers
- Slender components with densely packed reinforcements
- Sprayed concrete
- Textured surface finishes
- Pre-cast and pre-stressed concrete elements
- Bridges and cantilever structures

#### PRODUCT INFORMATION

<b>Chemical Base</b>	Organic Polymer Blend (SNF)
<b>Packaging</b>	275kg drum/ Bulk supply
<b>Appearance / Colour</b>	Brown liquid
<b>Shelf Life</b>	12 months from date of production
<b>Storage Conditions</b>	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +10 °C and +45 °C. Always refer to packaging.
<b>Density</b>	~1,22 kg/l at +25 °C
<b>pH-Value</b>	≥ 6

#### TECHNICAL INFORMATION

<b>Concreting Guidance</b>	The standard rules of good concreting practice, concerning production and placing are to be followed. Laboratory trials must be carried out before concreting on site, especially when using a new mix design or producing new concrete components. Fresh concrete must be cured properly and curing applied as early as possible.
----------------------------	---

#### CHARACTERISTICS / ADVANTAGES

- Improved workability
- Concrete is placed easily
- Especially suitable for slender components with densely packed reinforcement
- Improved compactability of concrete
- Improved cohesion of the concrete mix significantly reduces the risk of segregation

#### APPROVALS / STANDARDS

IS 9103, ASTM C494

## APPLICATION INFORMATION

<b>Recommended Dosage</b>	0,5–2,5% by weight of cement
<b>Compatibility</b>	Sikament® NN may be combined with many other Sika products. Trials must always be carried out before combining products in specific mixes. Contact Sika Technical Services for additional information and any specific combinations.
<b>Dispensing</b>	Sikament® NN is added to the gauging water or added with it into the concrete mixer. To achieve the optimum performance, a wet mixing time of at least 60 seconds is recommended. To avoid excess water in the concrete, the final dosage must begin after 2/3 of the wet mixing time.
<b>Restrictions</b>	Sikament® NN must not be added to dry cement.

## LIMITATIONS

Excessive water addition or overdosing may cause bleeding or segregation. When using Sikament® NN a suitable mix design has to be produced and the local material sources must always be trialed. If frozen and/or separation of the product has occurred, Sikament® NN may be used after thawing slowly at room temperature and intensive mixing. The w/b-ratio and consistence control remains the responsibility of the concrete producer. Laboratory trials are recommended to evaluate and confirm the actual water reduction. The chemical and physical composition of the components, concrete, Sikament® NN and concrete and ambient temperature can affect the setting time of the concrete.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika India Pvt. Ltd.**  
620, Diamond Harbour Road  
Commercial Complex II  
Kolkata - 700 034  
Tel : +91 33 24472448  
Fax : +91 33 23978688  
Mail : info.india@in.sika.com



**Product Data Sheet**  
**Sikament® NN**  
January 2020, Version 01.01  
021302011000000072

SikamentNN-en-IN-(01-2020)-1-1.pdf