

PRODUCT DATA SHEET

Sika® Sigunit® L-54 AF

ALKALI FREE LIQUID ACCELERATOR SHOTCRETE ADMIXTURE

DESCRIPTION

Sika® Sigunit® L-54 AF is an alkali free accelerator in liquid form for shotcrete applications.

USES

Sika® Sigunit® L-54 AF is a set accelerator suitable for both wet and dry spray applications.

Sika® Sigunit® L-54 AF is mainly used in :

- Securing of rock in tunnel mine construction.
- Rock and slope stabilisation
- High quality shotcrete for general construction work.

CHARACTERISTICS / ADVANTAGES

- Alkali free (non-caustic) and classified as non-toxic product.
- Very fast setting of shotcrete mixes
- No strength loss of the accelerated concrete if used correctly
- No additional contamination of mountain and ground water due to washed out alkalis
- Large reduction in rebound
- Improves bond of shotcrete to rock and concrete, making overhead spray easier.
- Free of chlorides, no danger to steel reinforcement and steel fibres.
- Low viscosity – less pumping problems

APPROVALS / STANDARDS

ASTM C 1141 Type I,II Grade 9 Class A

PRODUCT INFORMATION

Chemical Base	Mixture of special organic substances	
Packaging	300 Kg HDPE Drum	
Appearance / Colour	Beige white coloured suspension type liquid	
Shelf Life	6 months from date of production if stored in undamaged and unopened, original sealed containers.	
Storage Conditions	Store in dry condition,protected from direct sunlight and frost, at temperatures between +5°C and +35°C. Opened containers must be used as quickly as possible. It is recommended always stir well Sika® Sigunit® L-54 AF before use as with prolonged storage it can have a certain settlement as it is suspension type material	
Density	at +25 °C	1.40 – 1.44 kg/L
pH-Value	at +25 °C	1.5 – 3.5
Total Chloride Ion Content	No added chlorides	

SYSTEM INFORMATION

Compatibility

Sika® Sigunit® L-54 AF is compatible with all types Cements and standard cement replacement materials.
It is also compatible with the following Sika Product system Sikatards, Sikaments, Viscocrete, Sikaplast, SikaPump etc.

APPLICATION INFORMATION

Recommended Dosage

In general a dosage 3 - 10 % by weight of cementitious content.
The most effective dosage must be determined by site trials.

APPLICATION INSTRUCTIONS

DISPENSING

- Sika® Sigunit® L-54 AF is metered and added using a liquid dispensing system.
- Optimum dispersion in the shotcrete is governed by nozzle configuration and shotcreting techniques

LIMITATIONS

- The Sika® Sigunit® L-54 AF's effect depends on cement content, age, type and substrate.
- It is also dependent on the temperature of the shotcrete and the application area, and shotcrete methods used.
- The performance of the Sika® Sigunit® L-54 AF also significantly depends on, in the wet spray process, the w/c ratio of the basic concrete mix, and in the dry spray process, the amount of water added during spraying.
- Metal components that come into direct contact with the products should be fabricated of stainless steel. Do not use brass parts.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.

620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
Tel : +91 33 24472448
Fax : +91 33 23978688
Mail : info.india@in.sika.com



Product Data Sheet
Sika® Sigunit® L-54 AF
November 2018, Version 01.01
021401011000000044

SikaSigunitL-54AF-en-IN-(11-2018)-1-1.pdf