

BUILDING TRUST

PRODUCT DATA SHEET Sika[®] ViscoCrete[®]-7044 PR

High range water reducer / superplasticiser

DESCRIPTION

Sika[®] ViscoCrete[®]-7044 PR is a third generation High Range Water Reducing/SuperPlasticizing admixture for Ultra High Performance Concrete.

USES

Sika[®] ViscoCrete[®]-7044 PR is specially suitable for the production of concrete mixes which require high early strength development, powerful water reduction and excellent flowability

Sika[®] ViscoCrete[®]-7044 PR is mainly used for the following applications:

- Ready mixed concrete
- Precast concrete
- High performance concrete
- Ultra High Performance concrete
- Self Compacting Concrete (SCC)

CHARACTERISTICS / ADVANTAGES

Sika[®] ViscoCrete[®]-7044 PR as a powerful water reducer acts by through surface adsorption and sterical effects separating the binder particles the following properties are achieved:

- Poweful water reduction, resulting in high density, high strength and reduced permeability for water etc.
- Excellent plasticizing effect resulting in improved flowability, placing and compacting behaviour
- Reducded shrinkage and creep
- It does not contain chlorides or other ingredients promoting corrosion of steel reinforcement. It is therefore suitable for reinforced concrete.

APPROVALS / STANDARDS

Conforms to IS 9103 / ASTM C494

PRODUCT INFORMATION

Chemical base	Polycarboxylates Ethers
Packaging	255kg drum /bulk supply
Appearance / Colour	Light brown liquid
Shelf life	12 months from date of production
Storage conditions	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +40 °C. Protect from direct sunlight and frost. Always refer to the packaging. Frost: If frozen or if precipitation has occurred, the Product may be used after thawing slowly at room temperature and intensive mixing.
Density	~1.09 kg/l at 25°C
pH-value	≥ 6

Product Data Sheet Sika® ViscoCrete®-7044 PR February 2025, Version 01.01 021301011000005973

Recommended Dosage	 0.2 to 2% by weight of cementitious. The dosage rates given above are for typical usages, they are not meant as absolute limits, as other dosages may be utilized in special cases according to specific job conditions. Note: Preliminary laboratory trials are always recommended to determine the optimum consumption and injection parameters. Contact Sika Technical Services for additional information.
SYSTEM INFORMATION	
Compatibility	 The Product is compatible with all standard cement types. For use with other cements contact your local Sika technical service for information. The Product can be combined and is recommended for use with other Sika products, such as: Sika® Retarder setting retarders SikaRapid® hardening accelerators Sika® Stabilizer workability improver, for example Sika® Stabilizer VMA series to modify viscosity Sika© Control® durability and quality enhancer, for example SikaControl® AER series to improve frost and thaw resistance Sika® Antisol® curing compounds The Product is not compatible with admixtures from the Sikament® range. Always conduct trials before combining different products.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Excessive water addition or overdosing may cause bleeding or segregation.

If frozen and / or if precipitation has occurred, Sika® ViscoCrete®-7044 PR may be used after thawing slowly at room temperature and after intensive mixing.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

MIXING

The Product is a ready-to-use liquid that is added to the concrete during the mixing process. Optimal water reduction is obtained if the Product is dispensed into the concrete mix after the addition of 50–90 % of mixing water. Avoid adding the Product to dry materials. The Product should not be pre-mixed with other ad-

Product Data Sheet Sika® ViscoCrete®-7044 PR February 2025, Version 01.01 021301011000005973 mixtures. If other admixtures are to be used in concrete containing the Product they must be dispensed separately.

After adding the Product allow enough mixing time to secure a homogenous concrete. If necessary, continue mixing and add additional Product to obtain the required workability.

LOCAL RESTRICTIONS

Contact Sika Technical Services for additional information.

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.



LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd. 620, Diamond Harbour Road Commercial Complex II Kolkata - 700 034 West Bengal, India

Contact:

Phone: +91 33 2447 2448 Fax: +91 33 2397 8688 info.india@in.sika.com www.sika.in



Product Data Sheet Sika® ViscoCrete®-7044 PR February 2025, Version 01.01 021301011000005973 SikaViscoCrete-7044PR-en-IN-(02-2025)-1-1.pdf



BUILDING TRUST