

## PRODUCT DATA SHEET

# Sika® ViscoCrete® PH 9005

(formerly MasterPolyheed® 9005)

Water-reducing, high range, and retarding admixture based on modified poly-carboxylic ether

### DESCRIPTION

Sika® ViscoCrete® PH 9005 is an admixture of a new generation based on modified poly-carboxylic ether. The product has been primarily developed for applications in Ready-mix & Site-batched concrete where the highest performance is required.

### USES

- Ready mixed & Site mix Concrete
- Long-distance transporting
- Pumped concrete
- High workability without segregation or bleeding
- High performance concrete for durability
- Mixes requiring >20% water reduction
- Concrete containing pozzolans such as microsilica, GGBFS, PFA including high volume fly ash concrete

### PRODUCT INFORMATION

<b>Packaging</b>	245kg drum
<b>Shelf life</b>	12 months from date of production if stored properly in undamaged unopened, original sealed packaging.
<b>Storage conditions</b>	Sika® ViscoCrete® PH 9005 must be stored where temperatures do not drop below +5°C. If product has frozen, thaw at +5°C or above and completely reconstitute using mild mechanical agitation. Do not use pressurized air for agitation. Store under cover, out of direct sunlight and protect from extremes of temperature. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult your local Sika representative.
<b>Appearance / Colour</b>	Light to dark reddish brown liquid
<b>Density</b>	1.06 ± 0.02 at 25°C
<b>pH-value</b>	≥ 6

### APPLICATION INFORMATION

### CHARACTERISTICS / ADVANTAGES

- Good dispersion even in mixes with high cementitious fines
- Retains workability for long periods
- Lower pumping pressure
- Resistance to segregation even at high workability
- Reduced water content for a given workability
- Higher ultimate strengths
- Increased ease in finishing concrete

### APPROVALS / STANDARDS

IS 9103, ASTM C494 Type B,D,G

---

**Recommended Dosage**

Optimum dosage of Sika® ViscoCrete® PH 9005 should be determined with trial mixes. As a guide, a dosage range of 500ml to 1500ml per 100kg of cementitious material is normally recommended. Because of variations in concrete materials, job site conditions, and/or applications, dosages outside of the recommended range may be required. In such cases, contact your local Sika representative.

---

**Compatibility**

Sika® ViscoCrete® PH 9005 is compatible with most of the Sika products. Sika® ViscoCrete® PH 9005 is not compatible with Melamine or Naphthalene based admixtures and should not be used in conjunction in the same mix. Sika® ViscoCrete® PH 9005 is compatible with lingosulphonates and carboxylic acid-based plasticizer and retarders and also with most type of air entrainers, accelerators, retarders, extended set control admixtures, corrosion inhibitors, and shrinkage reducers. Sika® ViscoCrete® PH 9005 is also compatible with slag and pozzolans such as fly ash, metakaolin and silica fume.

---

**BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

**ECOLOGY, HEALTH AND SAFETY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

**LOCAL RESTRICTIONS**

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

**LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika India Pvt. Ltd.**

620, Diamond Harbour Road  
Commercial Complex II  
Kolkata - 700 034  
West Bengal, India

**Contact:**

Phone: +91 33 2447 2448  
Fax: +91 33 2397 8688  
info.india@in.sika.com  
www.sika.in

**Product Data Sheet**

Sika® ViscoCrete® PH 9005  
July 2024, Version 01.01  
02130100000002802

SikaViscoCretePH9005-en-IN-(07-2024)-1-1.pdf

