

PRODUCT DATA SHEET

Sika[®] Plastiment[®]-2001 NS

WATER REDUCING CUM INTEGRAL WATER PROOFING ADMIXTURE

DESCRIPTION

A liquid water reducing cum water proofing concrete admixture with a plasticizing effect.

USES

Sika[®] Plastiment[®]-2001 NS can be used for high quality concrete in difficult conditions such as:

- High temperature
- Long haul
- Ready mix concrete and
- Water proof concrete

CHARACTERISTICS / ADVANTAGES

Sika[®] Plastiment[®]-2001 NS provides the following beneficial properties :

- Long-lasting control of slump loss
- Very good for ready mix concrete plants where long haulage is there
- Improved workability without increasing water
- Reduced water without loss of workability
- Improved water tightness/water proofing
- Increased ultimate strength
- Improved surface finish

APPROVALS / STANDARDS

IS 9103, IS 2645

PRODUCT INFORMATION

Chemical Base	Modified Ligno Sulphonate
Packaging	255 kg/ Bulk supply
Appearance / Colour	Dark Brown Liquid
Shelf Life	12 months from date of production if stored properly in undamaged unopened, original sealed packaging.
Storage Conditions	Store in dry conditions at temperatures between +10°C and +40°C. Protect from direct sunlight and frost.
Density	~1.12 kg/l at 25°C
pH-Value	≥ 6

APPLICATION INFORMATION

Recommended Dosage	0.5% to 2.0% by weight of cement. Higher dosage may be used if agreed by engineer and consultant. Actual dosage to be finalised on the basis of site trials. Stir well before use.
Compatibility	Sika® Plastiment®-2001 NS may be combined with many other Sika® products. Compatible with all types of cements and cementitious materials. Important: Always conduct trials before combining products in specific mixes and combinations.

APPLICATION INSTRUCTIONS

DISPENSING

Sika® Plastiment®-2001 NS can be added into the mixing water or directly into the concrete mixer after 50 – 70% of the mixing water has been added. The addition of Sika® Plastiment®-2001 NS to dry aggregate or cement is not recommended. To achieve optimum performance a minimum wet mixing time, which is depending on the mixing conditions and the mixer performance, of 60 seconds is recommended.

LIMITATIONS

Excessive water addition or overdosing may cause bleeding or segregation. If frozen and / or if precipitation has occurred, Sika® Plastiment®-2001 NS may be used after thawing slowly at room temperature and after intensive mixing.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.
620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
Tel : +91 33 24472448
Fax : +91 33 23978688
Mail : info.india@in.sika.com



Product Data Sheet
Sika® Plastiment®-2001 NS
December 2018, Version 01.01
021302011000000903

SikaPlastiment-2001NS-en-IN-(12-2018)-1-1.pdf