

PRODUCT DATA SHEET

Sikafloor® QuartzTop-100

(formerly MTop 100)

Mineral dry-shake surface hardener for industrial floors.

DESCRIPTION

Sikafloor® QuartzTop-100 is a pre-mixed, dry-shake surface hardener, which contains hydraulic binder and high concentration of special graded mineral aggregates. Sikafloor® QuartzTop-100 contains pure silica sand.

Please note: The Product may only be used by experienced professionals only.

USES

Sikafloor® QuartzTop-100 is recommended for industrial floors with light to moderate traffic in:

- basements and cellars
- mechanical workshops
- garages for passenger cars
- storage rooms
- corridors, halls
- educational facilities
- parking areas
- loading platforms

PRODUCT INFORMATION

Packaging	25 kg bag.
Shelf life	Sikafloor® QuartzTop-100 can be stored for 12 months in the tightly closed original packages. Do not use the product if bag is damaged.
Storage conditions	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +30°C.
Appearance / Colour	Ready to use grey powder Other Colours available (Please consult with Sika representative)
Grain size distribution	0 – 2.36 mm
pH-value	> 12

CHARACTERISTICS / ADVANTAGES

Sikafloor® QuartzTop-100 offers following advantages:

- high abrasion resistance
- low level of porosity due to maximum compactness
- attractive
- easy to clean
- limited dust formation

APPROVALS / STANDARDS

CE marking and declaration of performance based on EN 13813:2002 Screed material and floor screeds — Screed material — Properties and requirements — Cementitious screed material

TECHNICAL INFORMATION

Abrasion resistance	450mg (500gm/1000 cycles/H-22)	(ASTM D 4060)
Surface hardness	7-8	(Moh's scale)
Resistance to impact	50% weight Loss (33MPa concrete has 70% loss of weight)	(LA Rattler)
Compressive strength	60 N/mm ² (70mm cube)	(ASTM C 109)

APPLICATION INFORMATION

Consumption	Loading condition	Consumption
	Light duty	3kg/m ²
	Midium duty	4kg/m ²
	Heavy duty	5kg/m ²

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Where operating and service conditions dictate the use of a metallic aggregate surface hardener for greater abrasion and impact resistance.
 - For use in areas exposed to acids and their salts or to materials known to deteriorate cement concrete, consult your local representative.
 - Do not apply over concrete with > 3% entrained air.
- Described technical properties are obtained in lab-conditions after 28 days at 23°C with 3 l water / 25 kg powder

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w).

APPLICATION INSTRUCTIONS

APPLICATION

1. Placing concrete
 2. Levelling, consolidating and striking off concrete
 3. Apply the first shake of Sikafloor® QuartzTop-100 manually or by spreader
 4. Floating the first shake of Sikafloor® QuartzTop-100 Repeat steps 3 up to 4 including (apply the second shake, floating the second shake of Sikafloor® QuartzTop-100) followed by a first trowelling and a second/final trowelling.
 5. Curing
 6. Sawing joints
 7. Application of joint sealant
- For detailed information on the application steps, please consult with Sika technical support or local representative.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.

620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
West Bengal, India

Contact:

Phone: +91 33 2447 2448
Fax: +91 33 2397 8688
info.india@in.sika.com
www.sika.in



SikafloorQuartzTop-100-en-IN-(09-2024)-2-1.pdf

Product Data Sheet

Sikafloor® QuartzTop-100
September 2024, Version 02.01
02081500000002036