

## PRODUCT DATA SHEET

# Sika MonoTop®-151 Migrating IN

Integral crystalline waterproofing for mortar and concrete (Formerly Sika®-101h)

## DESCRIPTION

Sika MonoTop®-151 Migrating IN is a cement based powder integral crystalline waterproofing system of hydrophilic nature for concrete and mortar to prevent water infiltration or seepage of water in the area of low pressure of concrete structure or any cementitious substrate. Sika MonoTop®-151 Migrating IN forms slurry consistency when mixed with water. When it is applied to the concrete substrate, it works as pore blocker and forms insoluble crystals inside water bearing capillaries and seals against further seepage of water.

## USES

Sika MonoTop®-151 Migrating IN is used as:

- Crystalline slurry coating
- Crystalline dry shake on concrete
- Crystalline integral waterproofing admixture for concrete or mortar

It is used for various waterproofing applications in:

- Reservoirs, bridges and dams
- Sewage water and effluent treatment plant
- Tunnel and underground subways
- Foundations, rafts and retaining walls
- Swimming pools and water tanks
- Underground parking structures
- Secondary containment structures
- Precast, insitu and shotcrete applications

## CHARACTERISTICS / ADVANTAGES

- Migration of active components and crystalline formation to seal capillary network
- Easy to apply
- For positive and negative side waterproofing
- Helps in faster construction schedule
- Can seal hairline cracks
- Becomes an integral and homogenous part of the structure
- Good adhesion to concrete
- Water vapour permeable
- Application on concrete and repair mortars
- No added chloride
- Non-toxic, suitable for use in potable water facilities
- Good mechanical properties
- Does not cause corrosion of steel reinforcement

## PRODUCT INFORMATION

<b>Product declaration</b>	Confirms to IS : 2645
<b>Chemical base</b>	Cement, selected aggregates, crystalline compounds and other additives
<b>Packaging</b>	30 kg bag
<b>Shelf life</b>	6 months from date of production

**Storage conditions** The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +40 °C. Protect from frost and humidity.

**Appearance / Colour** Grey powder

## TECHNICAL INFORMATION

**Water penetration after capillary absorption** Very low penetration under 5 bar pressure (EN 12390-8)  
NOTE: Crystalline compounds in Sika MonoTop®-151 Migrating IN penetrate into the concrete up to complete capillary depth available, in the process forming crystals and multiplying to keep sealing the capillaries bottom upwards constantly reducing the ingress of water. This takes some time to happen as the process of migration of the crystal forming compounds depend on various other factors like, quality and grade of concrete, cover of concrete, porosity of concrete, presence of free lime, etc. Hence minimum of 28 days of exposure of the coating under normal site conditions after application is recommended.

## APPLICATION INFORMATION

Mixing ratio	Application	Mixing ratio by weight
	Crystalline slurry coating - Horizontal	Sika MonoTop®-151 Migrating IN : Water = 3 : 1
	Crystalline slurry coating - Vertical	Sika MonoTop®-151 Migrating IN : Water = 5 : 2

Note: The mixing ratio can be slightly adjusted to meet site requirements.

**Fresh mortar density** ~2.1 kg/L (water : powder = 0.29)

Consumption	Application	Consumption
	Crystalline slurry coating - Horizontal	~1.10 kg/m <sup>2</sup>
	Crystalline slurry coating - Vertical	~0.70 kg/m <sup>2</sup> × 2 coats
	Crystalline dry shake	~1.8 kg/m <sup>2</sup>
	Crystalline integral waterproofing admixture	~0.8–1.0 % by weight of cement
	Crystalline waterproofing mortar - Construction joints	~1.60 kg/m <sup>2</sup>

Note: The consumption is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level or wastage, etc.

Note: Additional coats may be required as per clients specifications or site requirements.

**Ambient air temperature** +5 °C min. / +40 °C max.

**Substrate temperature** +5 °C min. / +40 °C max.

**Open time** ~40 min at +30 °C

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and con-

tains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### EQUIPMENT

#### Substrate preparation

- Mechanical or very high pressure water blasting

#### Mixing

- Low speed (< 500 rpm) hand drill mixer
- Mixing container

## Application

- Slurry brush
- Dry shake spreader / sieve

## Curing

- Water spray equipment, moist geotextile membrane, polyethylene sheet

## SUBSTRATE QUALITY

The concrete substrate shall be thoroughly clean, free from dust, loose material, surface contamination, cement laitance and material which reduce adhesion or prevent suction or wetting by the slurry coating.

## SUBSTRATE PREPARATION

- Surfaces should be prepared by acceptable preparation equipment to an open texture to achieve the required adhesion value for the waterproofing system.
- All connections between the substrate and pipe entries, plant and equipment, light switches etc, must be sealed and made watertight before applying Sika MonoTop®-151 Migrating IN.
- Any joints which are present in the structure must also be sealed and made watertight.
- Any visible cracks exceeding 0.5 mm wide must be sealed using appropriate methods.
- Area of honeycomb concrete and other surface imperfections must be repaired with polymer modified mortars.
- Wet surface until saturated.

## MIXING

### As a Crystalline Coating

1. Add Sika MonoTop®-151 Migrating IN to the requisite amount of water and stir with low speed single or double spindle mortar mixer at low speed (300-500 rpm) for 3-5 minutes until a lump free smooth brushable consistency is achieved. Note: Stir after subsequent intervals to ensure workability is maintained until open time.

### As an Integral Waterproofing Admixture

1. Sika MonoTop®-151 Migrating IN must be added to the concrete at the time of batching. The sequence of procedures for addition will vary according to the type of batch plant operation and equipment (for e.g. RMC dry batch operation, RMC central mix operation, site batching in 50 kg mixer, etc.). In all cases the objective should be to ensure complete dispersion of the powder in the mix.

## APPLICATION

### IMPORTANT

Do not apply on old rendered substrates.

### IMPORTANT

Protect the fresh mortar from rain, strong winds and direct sunshine at least 24 hours.

### IMPORTANT

Avoid protecting with plaster. When protecting with a plaster, clean surface using high speed water jet after approx. 28 days of application of final coating, followed by application of latex / acrylic bonding agent, scratch coat of plaster and final protection plaster. Please contact Sika Technical Services team for further guidance.

## IMPORTANT

When used as an admixture, in some cases little retardation is possible depending on the concrete mix design and the dosage rate of Sika MonoTop®-151 Migrating IN. Please consultant Sika Technical Services Team for advice.

### As Crystalline slurry coating:

1. Thoroughly saturate the prepared substrate before application with clean water to achieve a saturated surface dry (SSD) surface. Before application remove excess water, e.g. with a clean sponge.
2. Apply mixed material onto the prepared pre-wet substrate by suitable slurry brush by working the slurry well into the substrate and without the formation of voids.
3. Wherever applicable, a 2<sup>nd</sup> layer should be applied 'wet on wet' after allowing 1<sup>st</sup> layer to slightly stiffen to ensure full coverage of the surface and avoid 'pin-holes'.

### As Crystalline dry shake:

1. Spread uniformly the powder on saturated or green substrate through a sieve or a dry shake spreader.
2. Trowel the wet powder as the layer slightly sets.

### As Integral waterproofing admixture:

1. Add the powder at time of batching according to consumption.

## CURING TREATMENT

Protect fresh mortar immediately from premature drying using an appropriate curing method, e.g. water spray, moist geotextile membrane, moist hessian cloth, moist gunny bags, polyethylene sheet, etc. Cure at least for 5 days after application. For full cure approx. 28 days is recommended.

## CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened material can only be mechanically removed.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika India Pvt. Ltd.

620, Diamond Harbour Road  
Commercial Complex II  
Kolkata - 700 034  
West Bengal, India

### Contact:

Phone: +91 33 2447 2448  
Fax: +91 33 2397 8688  
info.india@in.sika.com  
www.sika.in



**Product Data Sheet**  
Sika MonoTop®-151 Migrating IN  
December 2023, Version 01.01  
020701010010000392

SikaMonoTop-151MigratingIN-en-IN-(12-2023)-1-1.pdf