

PRODUCT DATA SHEET

Sikament[®] RB 923 HY

(formerly MasterRheobuild[®] 923HY)

Retarding Superplasticising admixture for concrete

DESCRIPTION

Sikament[®] RB 923 HY is composed of synthetic polymers specially designed to impart rheoplastic qualities to concrete.

USES

Sikament[®] RB 923 HY is used for:

- Ready mixed concrete
- Long hauls
- Pumped concrete
- Concrete containing Granulated Slag/ Pozzolans
- Mass concrete pours
- Hot weather concreting

CHARACTERISTICS / ADVANTAGES

- Reduced thermal peaks
- High workability for longer periods
- Lower pumping pressure
- Resistance to segregation even at high workability
- Extended setting with longer workability
- Reduced water content for a given workability
- Higher ultimate strengths
- Reduced permeability
- Improved durability
- Reduced shrinkage and creep
- Increased ease in finishing concrete
- Provides lower in-place cost

APPROVALS / STANDARDS

Conforms to IS 9103 / ASTM C494 Type B, D, G

PRODUCT INFORMATION

Packaging	275 kg drum
Shelf life	12 months from date of production
Storage conditions	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight and frost. Always refer to the packaging. Frost: If frozen or if precipitation has occurred, the Product may be used after thawing slowly at room temperature and intensive mixing.
Appearance / Colour	Dark brown liquid
Density	1.19 ± 0.02 at 25°C
pH-value	≥ 6

TECHNICAL INFORMATION

Concreting Guidance	<ul style="list-style-type: none">▪ Follow the standard rules of good concreting practice for both production and placement.
----------------------------	--

- Carry out laboratory trials before concreting on site, especially when using a new mix design or producing new concrete components.
- Carry out trials to confirm the flowability and workability of the concrete.
- Cure fresh concrete properly and apply curing as early as possible, particularly in hot, windy and dry conditions, as well as at low temperatures.

Specific Advice

- Excessive water addition or overdosing may cause bleeding, segregation and extension of setting-times.
- Due allowance should be made for the effect of fluid concrete pressure on formwork, and stripping times should be monitored.
- The product ensures that the concrete remains workable for a certain period. Workability loss depends on the following aspects:
 - temperature,
 - type of cement,
 - nature of aggregates,
 - method of transport,
 - and initial workability.
- To achieve longer workability period please use a setting retarder from the Sika® Retarder series.

SYSTEM INFORMATION

Compatibility

The Product is compatible with most of the Sika products. The Product is compatible with all standard cement types. For use with other cements contact your local Sika technical service for information. The Product can be combined and is recommended for use with other Sika products, such as:

- SikaRapid® hardening accelerators
- Sika® Stabilizer workability improver
- SikaControl® durability and quality enhancer
- Sika® Separol® mould release agents
- Sika® Antisol® curing compounds

Always conduct trials before combining different products. Contact Sika Technical Services for additional information.

APPLICATION INFORMATION

Recommended Dosage

400ml to 1200ml per 100kg of cementitious material is recommended as a starting point.

The dosage rates given above are for typical usages, they are not meant as absolute limits, as other dosages may be utilized in special cases according to specific job conditions.

An overdosing may cause:

- Reduced permeability
- Long extension of initial and final set
- Increase in air entrainment

Note: Preliminary laboratory trials are always recommended to determine the optimum consumption and injection parameters.

Contact Sika Technical Services for additional information.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other

safety-related data.

APPLICATION INSTRUCTIONS

MIXING

The Product is a ready-to-use liquid that is added to the concrete during the mixing process. Optimal water reduction is obtained if the Product is dispensed into the concrete mix after the addition of 50–90 % of mixing water. Avoid adding the Product to dry materials. The Product should not be pre-mixed with other ad-

mixtures. If other admixtures are to be used in concrete containing the Product they must be dispensed separately.

After adding the Product allow enough mixing time to secure a homogenous concrete. If necessary, continue mixing and add additional Product to obtain the required workability.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.

620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
West Bengal, India

Contact:

Phone: +91 33 2447 2448
Fax: +91 33 2397 8688
info.india@in.sika.com
www.sika.in



SikamentRB923HY-en-IN-(07-2024)-1-1.pdf

Product Data Sheet

Sikament® RB 923 HY
July 2024, Version 01.01
02130200000002209