

## PRODUCT DATA SHEET

# Sikaplan® WT 5300-15 C

1.5 mm thick FPO sheet waterproofing membrane for pits and ponds

### DESCRIPTION

Sikaplan® WT 5300-15 C is a 1.5 mm thick sheet waterproofing membrane. It contains an inlay for restraint and is based on flexible polyolefin (FPO-PP).

### USES

The Product is designed for:

- Lining of irrigation ponds
- Lining of artificial lakes and canals
- Lining of leisure ponds and biotopes

Please note:

- The Product is not suitable for permanent exposure to liquids with temperatures above +35 °C.
- The Product is not suitable for potable water storage.

### CHARACTERISTICS / ADVANTAGES

- Proven performance over decades
- High UV stability
- Good resistance to microbial degradation
- High resistance to ageing

- Contains no fungicides, heavy metals, halogens or plasticisers
- Good tensile strength and elongation
- Good resistance to root penetration
- Suitable for contact with acidic (soft) water and alkaline environments
- Good resistance to bitumen
- Can be installed on wet substrates and on compacted soil
- Recyclable (Delete if recyclable facilities for product chemical base are not available in local country)

### APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to EN 13361 — Geosynthetic barriers — Characteristics required for use in the construction of reservoirs and dams
- CE Marking and Declaration of Performance to EN 13362 — Geosynthetic barriers — Characteristics required for use in the construction of canals
- CE Marking and Declaration of Performance to EN 13967 — Flexible sheets for waterproofing - Damp proofing and basement tanking

### PRODUCT INFORMATION

<b>Chemical base</b>	FPO/PP	
<b>Packaging</b>	Roll width	2 m
	Roll length	20 m
<b>Appearance / Colour</b>	Surface texture	smooth
	Colour	several colours available
Note: The membrane colour might change under the influence of UV-light around and above area of permanent water surface level if not properly covered with soil material.		
<b>Shelf life</b>	5 years from date of production	
<b>Storage conditions</b>	The Product must be stored in original unopened and undamaged sealed	

packaging in dry conditions and temperatures between +5 °C and +35 °C. Protect the Product from direct weather exposure. Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.

<b>Effective thickness</b>	1.50 mm (-0.07 mm / +0.15 mm)	(EN 1849-2)
<b>Mass per unit area</b>	1.30 kg/m <sup>2</sup> (-0.06 kg/m <sup>2</sup> / +0.13 kg/m <sup>2</sup> )	(EN 1849-2)

## TECHNICAL INFORMATION

<b>Resistance to static puncture</b>	> 1.6 kN	(EN ISO 12236)	
<b>Resistance to root penetration</b>	pass	(CEN/TS 14416)	
<b>Tensile strength</b>	<u>Longitudinal (MD)</u>	> 8 N/mm <sup>2</sup>	(EN ISO 527-3)
	<u>Transversal (CMD)</u>	> 7 N/mm <sup>2</sup>	
	<u>Longitudinal (MD)</u>	> 8 N/mm <sup>2</sup>	(EN 12311-2)
	<u>Transversal (CMD)</u>	> 7 N/mm <sup>2</sup>	
<b>Elongation at break</b>	<u>Longitudinal (MD)</u>	> 550 %	(EN ISO 527-3)
	<u>Transversal (CMD)</u>	> 550 %	
<b>Joint shear resistance</b>	> 350 N/50mm	(EN 12317-2)	
<b>Foldability at low temperature</b>	No cracks at -40 °C	(EN 495-5)	
<b>Coefficient of thermal expansion</b>	100 × 10 <sup>-6</sup> K <sup>-1</sup> ± 50 × 10 <sup>-6</sup> K <sup>-1</sup>	(ASTM D696)	
<b>Exposure to Bitumen</b>	<u>Bitumen compatibility</u>	<u>Watertight at 60 kPa</u>	(EN 1928; EN 1548)
<b>Resistance to oxidation</b>	<u>Change in tensile strength, aged 90 days at +85 °C</u>	< 10 %	(EN 14575)
	<u>Change in elongation, aged 90 days at +85 °C</u>	< 10 %	
<b>Microbiological resistance</b>	<u>Change in tensile strength, aged 16 weeks</u>	< 10 % (MD/CMD)	(EN 12225)
	<u>Change in elongation, aged 16 weeks</u>	< 10 % (MD/CMD)	

## SYSTEM INFORMATION

### System structure

### Ancillary products:

- Sikaplan® WT Fixation Plate PP
- Sikaplan® W Flat Profile Stainless Steel
- Sarnafil® T Prep
- Sarnafil® T Clean

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product

data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w).

## APPLICATION INSTRUCTIONS

IMPORTANT

### Strictly follow installation procedures

Strictly follow installation procedures as defined in Method Statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

## APPLICATION METHOD / TOOLS

IMPORTANT

### Application by trained personnel

The application of this Product must only be carried out by Sika® trained and/or approved contractors, experienced in this type of application. For information on substrate preparation and application, contact Sika Technical Services.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika India Pvt. Ltd.

620, Diamond Harbour Road  
Commercial Complex II  
Kolkata - 700 034  
West Bengal, India

### Contact:

Phone: +91 33 2447 2448  
Fax: +91 33 2397 8688  
info.india@in.sika.com  
www.sika.in



### Product Data Sheet

Sikaplan® WT 5300-15 C  
May 2026, Version 03.01  
020720201500000008

SikaplanWT5300-15C-en-IN-(05-2026)-3-1.pdf