

PRODUCT DATA SHEET

SikaPlast® PH 8156

(formerly MasterPolyheed® 8156)

Superplasticiser based on synthetic poly carboxylic ether

DESCRIPTION

SikaPlast® PH 8156 is an economical admixture based on synthetic poly carboxylic ether. The product has been primarily developed for applications in ready mix and site-batched concrete. SikaPlast® PH 8156 is specially designed to allow considerable reduction of mixing water while maintaining control on extend of set retardation.

SikaPlast® PH 8156 is free of chloride and has low alkali content. It is compatible with all types of cements.

USES

- Ready mixed concrete
- Long-distance transporting
- Pumped concrete
- High workability without segregation or bleeding
- High performance concrete for durability
- Congested/complex reinforced sections
- Mixes requiring >20% water reductions

CHARACTERISTICS / ADVANTAGES

- Good dispersion even in mixes with high fines
- High workability for longer periods
- Lower pumping pressure
- Resistance to segregation even at high workability
- Extended setting with longer workability
- Reduced water content for a given workability
- Higher ultimate strengths
- Increased ease in finishing concrete

Chemistry and mechanism of action

What differentiates SikaPlast® PH 8156 from the traditional superplasticisers is a new, unique mechanism of action that greatly improves the effectiveness of cement dispersion. Traditional superplasticisers based on melamine and naphthalene sulphonates are poly-

mers which are absorbed by the cement granules. They wrap around the granules surface areas at the very early stage of the concrete mixing process. The sulphonic groups of the polymer chains increase the negative charge of the cement particle surface and disperse these particles by electrical repulsion. This electrostatic mechanism causes the cement paste to disperse and has the positive consequence of requiring less mixing water to obtain a given concrete workability.

SikaPlast® PH 8156 has a different chemical structure from the traditional superplasticisers. It consists of a carboxylic ether polymer with long side chains. At the beginning of the mixing process it initiates the same electrostatic dispersion mechanism as the traditional Master Builders Solutions, but the side chains linked to the polymer backbone generates a steric hindrance which greatly stabilises the cement particles ability to separate and disperse. Steric hindrance provides a physical barrier (alongside the electrostatic barrier) between the cement grains. With this process, flowable concrete with greatly reduced water content is obtained.

APPROVALS / STANDARDS

ASTM C494 Type B,D,G , EN 934-2 T3.1/3.2, IS 2645-2003, IS 9103 -1999

PRODUCT INFORMATION

Packaging	245kg
Shelf life	12 months from date of production if stored properly in undamaged unopened, original sealed packaging.
Storage conditions	Store in dry conditions at temperatures between +5°C. Protect from direct sunlight and frost.
Appearance / Colour	Reddish brown liquid
Density	1.08 ± 0.02 at 25°C
pH-value	≥ 6

APPLICATION INFORMATION

Recommended Dosage	<p>Optimum dosage of SikaPlast® PH 8156 should be determined with trial mixes. As a guide, a dosage range of 300 ml to 1200ml per 100kg of cementitious material is normally recommended. To achieve water proofing qualities, water reduction in excess of 15% over control concrete is required. Because of variations in concrete materials, job site conditions, and/or applications, dosages outside of the recommended range may be required. In such cases, contact your local Sika representative.</p> <p>For additional information on SikaPlast® PH 8156 admixture or on its use in developing concrete mixes with special performance characteristics, contact your local Sika representative.</p> <p>Effects of over dosage</p> <p>A severe over-dosage of SikaPlast® PH 8156 can result in the following:</p> <ul style="list-style-type: none">Reduced permeabilityLong extension of initial and final setIncrease in air entrainment <p>A slight overdosing may not adversely affect the ultimate strength of the concrete and can achieve higher strengths than normal concrete, provided it is properly compacted and cured. Due allowance should be made for the effect of fluid concrete pressure on form work, and stripping times should be monitored.</p> <p>In the event of over dosage, consult your local Sika representative immediately.</p>
Dispensing	<p>SikaPlast® PH 8156 is a ready-to-use liquid which is dispensed into the concrete together with the mixing water. The plasticising effect and water reduction are higher if the admixture is added to the damp concrete after 50 to 70% of the mixing water has been added. The addition of SikaPlast® PH 8156 to dry aggregate or cement is not recommended.</p> <p>Thorough mixing is essential and a minimum mixing cycle, after the addition of the SikaPlast® PH 8156, of 60 seconds for forced action mixers is recommended.</p>
Compatibility	<p>SikaPlast® PH 8156 is compatible with most of the Sika products. SikaPlast® PH 8156 is not compatible with Melamine or Naphthalene based admixtures and should not be used in conjunction in the same mix. SikaPlast® PH 8156 is compatible with ligno- sulphonates and carboxylic acid based plasticiser and retarders and also with most type of air- entrainers, accelerators, retarders, extended set- control admixtures, corrosion inhibitors, and shrinkage reducers. SikaPlast® PH 8156 is also compatible with slag and pozzolans such as fly ash, metakaolin and silica fume</p>

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may

vary due to circumstances beyond our control.

FURTHER DOCUMENTS

CORROSIVITY – NON CORROSIVE

SikaPlast® PH 8156 admixture will neither initiate nor promote corrosion of reinforcing steel embedded in concrete, prestressed concrete or concrete placed on galvanized steel floor and roof systems. Neither calcium chloride nor any calcium chloride-based ingredients are used in the manufacture of SikaPlast® PH 8156 admixture. In all concrete application, SikaPlast® PH 8156 admixture will conform to the most stringent or minimum chloride ion limits currently suggested by construction industry standards and practices.

WORKABILITY

SikaPlast® PH 8156 ensures that rheoplastic concrete remains workable for a longer time. Workability loss is dependent on temperature, and on the type of cement, the nature of aggregates, the method of transport and initial workability. It is strongly recommended that concrete should be properly cured particularly in hot, windy and dry climates

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika India Pvt. Ltd.

620, Diamond Harbour Road
Commercial Complex II
Kolkata - 700 034
West Bengal, India

Contact:

Phone: +91 33 2447 2448
Fax: +91 33 2397 8688
info.india@in.sika.com
www.sika.in



Product Data Sheet

SikaPlast® PH 8156
July 2024, Version 01.01
02130100000002139

SikaPlastPH8156-en-IN-(07-2024)-1-1.pdf